

Ceramic Anti-Spatter Spray



High-temperature-resistant release agent | protective coating for MIG/MAG welding processes

WEICON Ceramic Anti-Spatter Spray is a high-grade release agent and lubricant, which is suitable for extremely high pressures and temperatures. The spray is a ceramic protective coating for MIG/MAG welding processes. It forms an anti-spatter dry film, which prevents the adhesion of welding spatter. That way, welding tips and gas nozzles are protected. The use of the spray minimises downtimes and interruptions in the production process to clean the welding equipment. Ceramic Anti-Spatter spray is silicone-free. It protects welding heads on welding robots, welding tips and gas nozzles as well as sensitive equipment, cables, sensors etc. against the adhesion of welding spatters. It is also suitable for applications in plasma and laser cutting, brazing, aluminium extrusion, the foundry industry, sinter metallurgy, the glass industry and high-temperature furnace construction.

Technical data

Base	Ceramic/boron nitride	
Odour	solvent	
Colour	white	
Texture	sprayable	
Silicone-free	yes	
Binder	organic	
Minimum shelf life	at room temperature	24 mon.
Density	env. 1,2 g/ml	
Solid content	(without propellant)	42 %
Application temperature	900 °C air < 1,600 °C vacuum, inert gas *Binder decomposes > 120 °C	
Compatible with Double Nozzle	no	

Application

Apply to welding nozzles from approx. 15 cm. To protect the surface of the workpiece, spray it from approx. 25 cm and approx. 10 cm to the right and left of the weld seam. In hollow bodies and confined spaces, do not start welding until the propellant has evaporated.

Storage

Container is pressurised. Protect from direct sunlight and temperatures above +50 °C.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

10060631 Ceramic Anti-Spatter Spray, 400 ml, white

Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{mm}/25.4 = \text{inch}$
 $\mu\text{m}/25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N}/\text{mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$

$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$
 $\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
 $\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Colombia S.A.S
Colombia
Phone: +57 314 793 86 06
Email: info@weicon.co

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.L.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr