

Surface and anti-corrosion coating

Zinc Spray bright grade

Long-term cathodic corrosion protection | bright colour shade matching hot-dip galvanization

WEICON Zinc Spray "bright grade" is approved by the German TÜV and provides all metal surfaces with a long-lasting cathodic corrosion protection. It has a bright colour shade matching fresh hot-dip galvanization. It forms a fast-drying, adherent protective layer of microfine zinc flakes. The zinc flakes form a resistant protective layer even against extreme weather and environmental conditions. Even after more than 550 hours in the salt spray test according to DIN EN 9227, metal parts coated with WEICON Zinc Spray "bright grade" did not show any corrosion.

WEICON Zinc Spray "bright grade" can be used for the coating of welded joints and drill holes, as a conductive intermediate layer for spot welding and wherever metal must be protected against corrosion.

Technical data

Colour	matching hot-dip galvanizations	
Application area	indoor and outdoor use	
Binder	modified acrylic resin	
Pigment	flaky zinc and aluminium pigments	
Pigment purity	ca. 99.9% Zn / ca. 99.5% Al	
Metal content in dry film	~70 %	
Processing temperature	+5°C to +35°C, ideally +18°C to +35°C	
Recommended primer	Zinc Spray	
Consumption	per 1.5 crosswise application	150 ml/m ²
Layer thickness with 1.5 crosswise applications approx.	20 - 40 µm	
Dust-dry	15 min.	
Cured after	10-12 h	
Paintable	after 24 h	
Cross cutting	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Abrasion-resistant	yes	
Cylindrical mandrel bend test	DIN EN ISO 1519	no hairline cracking
Topcoat	not required	
Density	1,0 g/cm ³	
Temperature resistance	-50°C to +300°C	
Shelf life	24 mon.	

Approvals / Guidelines

ISSA Code	53.402.07
IMPA Code	450812
IKS	DIN EN ISO 9227-NSS / 576 hours

Surface pre-treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Processing

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20°C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

10000047 Zinc Spray bright grade, 400 ml

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr