

## Surface and Anti-Corrosion Coating

# Galva-Spray



**Long-lasting cathodic corrosion protection | colour matched to fresh hot-dip galvanising**

WEICON Galva Spray serves as permanent protective layer for all metal surfaces. It protects metals against rust and corrosion and is fast-drying and strongly adherent. The spray is resistant to salt water and fresh water and temperatures up to +300 °C (+572 °F). After more than 450 hours in the salt spray test according to DIN EN 9227, metal parts coated with WEICON Galva Spray did not show any corrosion. The spray can be used for repairing hot galvanized parts with matching colours, as highly effective antirust primer, e.g. for car bodypainting, as coating on welded joints and drill holes, and as conductive intermediate layer in spot-welding.

### Technical data

Colour	matching hot-dip galvanizations	
Application range	indoor and outdoor use	
Binder	Acrylate resin	
Pigment	zinc and aluminium pigments	
Pigment purity	ca. 99.5% Al / ca. 94.0% Zn	
Metal content in dry film	~51 %	
Processing temperature	+5 °C to +35°C, ideally +18 °C to +25°C	
Recommended primer	Zinc Spray	
Consumption	per 1.5 crosswise application	~ 2 m <sup>2</sup>
Layer thickness with 1.5 crosswise applications approx.	20 - 40 µm	
Dust-dry after	15 min.	
Minimum shelf life	at room temperature	24 mon.
Cured after	10-12 h	
Can be painted	after 12 h	
Grid cut	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Abrasion-resistant	yes	
Mandrel bending test	DIN EN ISO 1519	no hairline cracking
Top coat	not required	
Density	0,9 g/cm <sup>3</sup>	
Temperature resistance	-50°C to +300°C	

### Approvals / Guidelines

IKS	DIN EN ISO 9227-NSS / 450 hours	
-----	---------------------------------	--

### Surface Pre-Treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

### Application

Shake can before use until the mixing ball can be heard clearly. Spray on evenly and crosswise at room temperature (approx. 20 °C) and at about 25 cm distance from the surface. Dust-dry after approx. 15 minutes, fully hardened after approx. 10-12 hours.

### Storage

Container is pressurised. Protect from direct sunlight and temperatures above +50 °C.

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

### Available sizes

10040054 Galva-Spray, 400 ml

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquaters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr