

Surface and Anti-Corrosion Coating

Rust Protection 2000 PLUS



Special corrosion- and weatherresistant surface coating

WEICON Rust Protection 2000 PLUS is a particularly corrosion- and weather-resistant surface coating based on ferric oxide (hematite). By using highly-pure iron oxide pigments in a flaky arrangement, permanent weather-resistant and water-repellent surface protection is achieved. It can be used wherever metallic constructions or installations need long-term and visually appealing protection against extreme environmental and weather conditions. WEICON Rust Protection 2000 PLUS can be used on hall and steel structures, iron railing, lattice towers, fences, handrails, balcony grates, rolling gates, outdoor lights, and on all components vulnerable to corrosion.

Technical data

Colour	Anthracite / DB 703, silver-grey / DB 701	
Application range	indoor and outdoor use	
Binder	Alkyd resin	
Pigment	Lamellar hematite	
Pigment purity	> 90% iron oxide	
Metal content in dry film	~58 %	
Processing temperature	+5 to +35°C, ideally +18 to +35°C	
Recommended primer	not required	
Consumption	per 1.5 crosswise application	~ 2 m ²
Layer thickness with 1.5 crosswise applications approx.	60 - 80 µm	
Dust-dry after	30 min.	
Minimum shelf life	at room temperature	24 mon.
Cured after	24 h	
Can be painted	after 24 h	
Grid cut	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Abrasion-resistant	yes	
Mandrel bending test	DIN EN ISO 1519	no hairline cracking
Top coat	not required	
Density	1,3 g/cm ³	
Temperature resistance	-50°C to +300°C	

Approvals / Guidelines

ISSA Code	53.402.40/41
-----------	--------------

Surface Pre-Treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Application

Shake can well for two minutes before use, until the mixing pea is clearly audible. Keep shaking the can briefly every now and then during the application. Apply Rust Protection 2000 PLUS at room temperature (approx. +20 °C) from a distance of approx. 25 cm evenly in two crosswise layers.

Storage

Container is pressurised. Protect from direct sunlight and temperatures above +50 °C.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

- 10021353 Rust Protection 2000 PLUS, 400 ml, anthracite
- 10021354 Rust Protection 2000 PLUS, 400 ml, grey

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr