

Copper Spray

High-quality and effective

WEICON Copper Spray is a high-quality, weather-resistant metal spray with high adhesive strength and a high copper content for protective and decorative coatings with an appealing non-ferrous metal character for indoor and outdoor use. It is even used for the optical refinement (copper-plating) of various material surfaces or design parts. Copper Spray can be used on window sills, gutters and downspouts, outdoor lights and mailboxes, as well as for arts and crafts and decorative work.

Technical data

Colour	copper-metallic, matt	
Silicone-free	yes	
Application range	indoor and outdoor use	
Binder	Acrylate resin	
Pigment	copper pigments	
Pigment purity	ca. 99.9% Cu	
Metal content in dry film	~50 %	
Processing temperature	+5 to +35°C, ideally +18 to +35°C	
Recommended primer	Zinc Spray	
Consumption	per 1.5 crosswise application	~ 2 m ²
Layer thickness with 1.5 crosswise applications approx.	20 - 30 µm	
Dust-dry after	10 min.	
Minimum shelf life	at room temperature	24 mon.
Cured after	4-6 h	
Can be painted	after 4 h	
Grid cut	DIN 53151/ISO 2409	Cross cutting test value 0 to 1
Abrasion-resistant	yes	
Mandrel bending test	DIN EN ISO 1519	no hairline cracking
Top coat	not required	
Density	0.9 g/cm ³	
Temperature resistance	-50°C to +300°C	

Approvals / Guidelines

MIL-Spec	complies with	MIL-T-83523
----------	---------------	-------------

Surface Pre-Treatment

Clean and degrease surfaces with WEICON Surface Cleaner.

Application

Shake can before use, until the mixing pea is clearly audible. Apply evenly at room temperature (approx. +20°C / +68°F) from a distance of approx. 25 cm in crosswise layers. Dust-dry after 10 min., fully cured after approx. 4-6 hours.

Storage

Container is pressurised. Protect from direct sunlight and temperatures above +50 °C.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

10060386	Copper Spray, 400 ml
10000140	Copper Spray, 400 ml

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON Iberica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
Phone +90 (0) 212 465 33 65
info@weicon.com.tr