

# Adhesive Spray

## Adhesive Spray

### Universal use

WEICON Adhesive Spray is suitable for all-purpose use and bonds light materials. WEICON Adhesive Spray is suitable for the bonding of numerous materials such as paper, cardboard, pasteboard, wood, thin veneers, cork, leather, textiles, felt, soft foam, rubber, foam rubber, and plastic film (except for PVC and polyethylene). It is especially suited for the bonding of hard foam.

### Technische Daten

Base	synthetic rubber
Silicone-free	yes
Processing temperature	+10°C to +30°C
Consumption per 1.5 crosswise application	~ 13 m <sup>2</sup>
Evaporation time	5 - 15 min.
Temperature resistance	-20°C to +65°C
Shelf life	12 mon.

### Processing

1. Shake can before use. Surfaces must be dry, clean and free of

grease. Spray on one surface at about 15 to 30 cm distance. With

porous materials, Adhesive Spray should be applied on both surfaces.

2. Depending on surface characteristics and ambient temperature,

let the spray dry for 1 - 15 minutes until the adhesive is no longer stringy.

3. Position the parts and join them with strong pressure.

4. The spray head can be set to horizontal or vertical spray jet

### Storage

Pressurized container. Protect from direct sunlight and temperatures above +50°C.

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes

10059961 Adhesive Spray, 500 ml

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr