Silicone N



Neutral-curing | fungicidal

WEICON Silicone N is free of solvents, neutrally vulcanizing, strong, permanently elastic, resistant to weathering, ageing and chemicals, temperature-resistant up to +180 °C (+356 °F), extremely elastic (breaking elongation of approx. 550%) and can be used universally. Silicone N adheres very well to all metals, glass, ceramics, and many other materials.

Silicone N can be used in plastic processing, the electrical industry, energy technology, the lighting industry, exhibition construction and shopfitting, and in many other industrial areas.

Characteristics		
Base		1-C. polysiloxane (oxime)
Texture		pasty
Colour		transparent
Cure type		moisture-curing
Can be painted after		no
Stability/run-off	ASTM D 2202	1.0 mm
Building material class	DIN 4102	B 2
Minimum shelf life	at room temperature	18 mon.
Processing		
Curing condition		from +5°C to +40°C and 30% to 95% rel. air air humidity
Curing speed	in the first 24 h	2 -3 mm
Density	(+23 °C) ISO 1183-1	1,0 g/cm³
Max. sealing joint width		25 mm
Gap bridging up to max.		5 mm
Curing		
Skin-over time		7 min.

Mechanical properties after curing		
Tensile strength	ISO 37	1,5 N/mm²
Elongation at break (tensile)	ISO 37, S3A	550 %
Elongation at 100 %	ISO 37 S3A	0,4 N/mm²
Movement absorption max.		25 %
Hardness (Shore A)	DIN ISO 7619	20±5
Volume change	DIN 52451	<-6 %
Thermal parameters		
Temperature resistance		-40°C to +180°C
Electrical parameters		
Resistance		1·10^12 Ω·m
Dielectric strength		17,0 kV/mm
Approvals / Guidelines		
MIL-Spec	complies with	MIL-A-46146B Group I Type 1

Surface pretreatment

Surfaces must be clean and free of grease. Many surface soilings, such as oil, grease, dust and dirt can be removed with WEICON Surface Cleaner. For heavily soiled metal surfaces, we recommend Cleaner Spray S; for removing old colour residues or adhesive residues, WEICON Sealant and Adhesive Remover is ideal. Most materials can be bonded to and among each other. For certain materials or special requirements, we recommend the use of a bonding agent (primer). Mechanical surface pre-treatment e.g. by grinding or sanding can also improve the adhesion considerably.

Application

Application methods

Hand-operated caulking gun for 310 ml cartridges, pneumatic caulking gun (we recommend only a piston-rod version, such as the WEICON pneumatic cartridge gun), automatic dispensing systems.

Joining the adhesive parts

To ensure optimal wetting, the adhesive parts must be joined before the first skin forms on the adhesive (skin formation time).

Storage

Store in the unopened original container at room temperature. Avoid sources of heat and direct sunlight.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquaters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Colombia S.A.S
Colombia
Phone: +57 314 793 86 06
Email: info@weicon.co

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.L.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

Elastic adhesives and sealants
Silicones

Silicone N

Accessories

10025241 V-Joint Nozzle, 1 PCE
10020751 Cartridge Gun Special, 1 PCE
10000441 Cartridge Gun, 1 PCE
10101992 Clip Nozzle Green Tube, 1 PCE, transparent
10059792 Pressure gun Airflow 3, 1 PCE

Available sizes

10105011 Silicone N, 280 ml (Green Tube), transparent
10105014 Silicone N, 280 ml (Set), transparent

To the product detail page:

Chemical resistance after curing* (Excerpt)

Acetaldehyde	-	Methanol	o
Acetone	o	Methyl ethyl ketone (MEK)	o
Formic acid >10 % (methanoic acid)	o	Lactic acid 40 %	+
Ammonia 10 %	+	Engine oil min./synth.	o
Ammonia, anhydrous	-	Sodium carbonate (soda)	+
Aniline	-	Sodium hydroxide solution 10 %	o
Petrol (92-100 octane)	-	Phosphoric acid 5 %	o
Acetic acid 10 %	+	Nitric acid <5%	o
Acetic anhydride	-	Hydrochloric acid <10 %	o
Ethanol	+	Concentrated hydrochloric acid	-
Ethylene glycol	+	Salt water / Sea water	+
Antifreeze	+	Sulphuric acid 10 %	+
Gear oil	-	Concentrated sulphuric acid	-
Glycerine / Glycol	+	Silver nitrate	+
Hexane	-	Cooking oil / vegetable oil	+
Hydraulic oil	o	Toluene	-
Isopropanol	+	Water	+
Potassium hydroxide 10 %	+	Tartaric acid	+
Potassium hydroxide 20 %	-	Xylene	-
Potassium salt dry	+	Citric acid 10 %	+
Coolant, aq.	+	Heating oil, diesel	-

+ = resistant 0 = for a limited time (preliminary tests or resistance tests are recommended) - = not resistant *Storage was carried out at a chemical temperature of +20°C.

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquaters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Colombia S.A.S
Colombia
Phone: +57 314 793 86 06
Email: info@weicon.co

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.L.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr