

Anti-Seize High-Tech Spray



Nonfood Compounds
Program Listed H1
Registration 141636

Metal-free | NSF registration

WEICON Anti Seize "High-Tech" is high-temperature-resistant, has excellent separating characteristics, is metal-free, neutral to materials and has an NSF approval. Anti-Seize High-Tech is dry lubricant paste for metal screw connections and particularly suitable when metal-containing pastes can cause electrolytic reactions, when nickel-containing products should or may not be used due to health reasons and when dark metal-containing products should or may not be used for visual reasons.

Technische Daten

Base		medical white oil
Colour		white
Density	(+20°C) DIN 51757	1,42 g/cm ³
Silicone-free		yes
Four ball weld test property load	DIN 51350	3.600 N
Four ball weld test weld load	DIN 51350	3.800 N
Four ball weld test calotte value	DIN 51350 (1min/1000N)	0,7 mm
Cone penetration	DIN ISO 2137	310 - 340 1/10 mm
Water resistance	DIN 51807	1 - 90
Pressure		230 N/mm ²
Thermal conductivity		0,7 W/m·K
Dielectric strength	DIN EN 60243-1 (20°C)	0,4 kV/mm
Temperature resistance		-40°C to +1,400°C
Approvals / Guidelines		
ISSA Code		53.402.19

Reibwerte

Reibwerte Stahl-blank		
Total friction coefficient		0,11 (min. 0,10)
Friction coefficients threads		0,12 (min. 0,10)
Friction coefficient head		0,10 (min. 0,09)
Reibwert V4A		
Total friction coefficient		0,15 (min. 0,14)
Friction coefficients threads		0,15 (min. 0,13)
Friction coefficient head		0,15 (min. 0,14)
Reibwert Stahl galvanisch verzinkt		
Total friction coefficient		0,08 (min. 0,07)
Friction coefficient threads		0,09 (min. 0,08)
Friction coefficient head		0,07 (min. 0,06)

Surface pre-treatment

First clean the surface to be lubricated with WEICON Cleaner S, depending on the degree of soiling. If screws have already been used, process with the wire brush and clean with WEICON Cleaner S. For a better spray function, warm the product up to room temperature.

Processing

Shake can until mixing pea is audible. Spray on from a distance of approx. 15 cm. ASW 400 is only suitable for active substance-specific use, it does not replace oil or grease lubrication.

Storage

Store in tightly closed original container. Do not store with oxidising agents. Store at room temperature in a dry place. Original sealed containers have a shelf life of 24 months.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Available sizes

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Turkey
phone +90 (0) 212 465 33 65
info@weicon.com.tr