

WEICONLOCK® AN 301-65 Pipe and Flange Sealing



Pipe and flange sealing with PTFE | classified as non-hazardous | drinking water approval

- high viscosity
- medium strength
- disassembly with normal tools

Technical Data

Colour	white
Fluorescent	no
For thread connections up to	M 80 R 3"
Viscosity	180.000 - 300.000 mPa·s
Gap bridging up to max.	0,5 mm
Breakaway torque	4 - 8 Nm
Prevail torque	1 - 3 Nm
Shear strength Nmm ² (DIN 54452)	2 - 6 N/mm ²
Handling strength	10 - 20 min.
Final strength (100 % strength)	24 h
Temperature resistance	-60°C to +150°C
Minimum shelf life	at room temperature
Compressive strength (free cutting steel / grub screw = 8.8)	24 mon.
M 3x6	max.
M 4x6	max.
M 5x8	max.
M 6x10	max.
M 8x12	max.
M 10x16	max.

Approvals / Guidelines

MIL-Spec	complies with	MIL-A-46106
----------	---------------	-------------

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 551 9322 0
info@weicon.de

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr