

# WEICONLOCK® AN 302-25 Pipe and thread sealing



## Pipe and thread sealing | vibration-proof for coarse threads

- high viscosity
- low strength
- easy disassembly

### Technical Data

Colour	brown	
Fluorescent	no	
For thread connections up to	M 80 R 3"	
Viscosity	6.000 - 30.000 mt mPa·s	
Gap bridging up to max.	0,3 mm	
Breakaway torque	5 - 8 Nm	
Prevail torque	2 - 4 Nm	
Shear strength Nmm <sup>2</sup> (DIN 54452)	3 - 5 N/mm <sup>2</sup>	
Handling strength	15 - 30 min.	
Final strength (100 % strength)	3-6 h	
Temperature resistance	-60°C to +150°C	
Compressive strength (free cutting steel / grub screw = 8.8)		
M_3x6	max.	1500 bar
M_4x6	max.	1500 bar
M_5x8	max.	1500 bar
M_6x10	max.	1000 bar
M_8x12	max.	800 bar
M_10x16	max.	400 bar

## Anaerobic Adhesives and Sealants

### Surface pre-treatment

Clean surfaces to be sealed.

### Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. Apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. When used as flange sealing, apply a continuous bead to one flange side, then assemble parts quickly and screw tight. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

### Storage

Shelf life: at least 24 months at room temperature (+20°C).

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Accessories

- 10021433 Activator F, 200 ml, green
- 10001256 Dosing Tip, 1 PCE

### Available sizes

- 10019893 WEICONLOCK® AN 302-25 Pipe and thread sealing, 200 ml, brown
- 10019891 WEICONLOCK® AN 302-25 Pipe and thread sealing, 50 ml, brown

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
[info@weicon.ae](mailto:info@weicon.ae)

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
[info@weicon.cz](mailto:info@weicon.cz)

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
[info@weicon.de](mailto:info@weicon.de)

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
[office@weicon.com](mailto:office@weicon.com)

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
[info@weicon.com.sg](mailto:info@weicon.com.sg)

WEICON Inc.  
Canada  
phone +1 877 620 8889  
[info@weicon.ca](mailto:info@weicon.ca)

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
[info@weicon.es](mailto:info@weicon.es)

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
[info@weicon.it](mailto:info@weicon.it)

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
[info@weicon.co.za](mailto:info@weicon.co.za)

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Turkey  
phone +90 (0) 212 465 33 65  
[info@weicon.com.tr](mailto:info@weicon.com.tr)