

WEICON Easy-Mix HT 180 Epoxy Adhesive



High temperature resistance | steady | shock- and impact resistant

WEICON Easy-Mix HT 180 is a 2-component adhesive based on epoxy resin with high temperature resistance up to +180 °C (+356 °F); short-term up to +230 °C (+446 °F). The adhesive is highly viscous and stable which also makes it suitable for vertical applications. It is impact- and shock-resistant, has a long pot life, cures at room temperature and is machinable after curing. The adhesive is particularly suitable for the bonding of composite materials and metal and can be spot-welded while curing. Easy-Mix HT 180 can also be used on plastics, ceramics, glass, stone or wood and is suitable for adhesions where larger tolerances have to be bridged. Due to special fillers, it is possible to achieve a non-varying and reliable adhesive joint of at least 0.20 - 0.25 mm. The high temperature resistance enables the bonding of components, which are thermo-coated (powder-coated) after curing.

Characteristics

Base	Epoxy resin, mineral-filled	
Texture	pasty, gap-filling	
Colour	black	
Minimum shelf life	at room temperature	24 mon.

Processing

Processing temperature	+10 °C to +40 °C	
Curing temperature	+10 °C - +50 °C	
Mixing ratio by weight	2:1	
Density of the mixture	1,1 g/cm³	
Gap bridging up to max.	4 mm	

Curing

Pot life	at 20 °C, 10 ml batch	60 min.
Handling strength	(35 % strength)	120 min.
Working strength after	(50 % strength)	4 h
Final strength	(100 % strength)	24 h
Shrinkage		0,3 %

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

Epoxy Resin Systems

Epoxy adhesives

Mechanical properties after curing

Tensile strength	DIN EN ISO 527-2	27 MPa
E-modulus (tensile)	DIN EN ISO 527-2	2.300 - 2.700 MPa
Compressive strength	DIN EN ISO 604	52 MPa
Bending strength	DIN EN ISO 178	46 MPa
Hardness (Shore D)	DIN ISO 7619	80

Lap shear strength material thickn. 1,5mm DIN EN 1465

Steel 1.0338 sandblasted	23 N/mm²
Stainless steel V2A sandblasted	24 N/mm²
Aluminium sandblasted	13 N/mm²
Galvanized steel	8 N/mm²
PVC-rigid roughened	11 N/mm²
CFRP	22 N/mm²

Thermal parameters

Temperature resistance	-50 °C to 180 °C, briefly up to +230 °C	
Tg after curing at room temperature	(DSC)	54,4 °C
Tg after tempering (at 120°C)	(DSC)	44,7 °C
Temperature conductivity	0,172 mm²/s	
Thermal conductivity	DIN EN ISO 22007-4	0,26 W/m·K
Heat capacity	DIN EN ISO 22007-4	1,335 J/(g·K)

Electrical parameters

Resistance	DIN EN 62631-3-1	2,48 · 10 ¹¹ Ω·m
Dielectric strength	DIN EN 60243-1 (20°C)	18 kV/mm

Approvals / Guidelines

ISSA Code	75.530.04	
IMPA Code	812923	
MIL-Spec	complies with	MIL-A-47284A

Instructions for use


When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

WEICON Easy-Mix HT 180 Epoxy Adhesive

Epoxy Resin Systems

Epoxy adhesives

Tensile strength after storage



Surface Pre-Treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner).

Application

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5 °C and below, no reaction takes place.

Storage

WEICON epoxy adhesives should be stored in a dry place at room temperature. Unopened containers can be stored at temperatures from +18 °C to +25 °C. Protect from direct sunlight. Failure to observe these storage instructions will reduce the shelf life to 6 months. Epoxy resins generally tend to crystallise at temperatures below +5 °C. This effect is increased by large temperature fluctuations, e.g. during transport especially in the winter months. This has a negative impact on processing, curing and technical data, can, however, be reversed by heating the product (up to max. +50 °C, no open flame). In WEICON epoxy adhesives, crystallisation is reduced by the careful choice and combination of base resins (bisphenol A and F).

Scope of delivery

Adhesive | Helix Mixing Nozzle A

Accessories

10005237 Dispenser Easy-Mix D 50, 1 PCE
 10101999 WEICON Manual Dispenser, 1 x 1:1 | 2:1
 10026925 Helix Mixing Nozzle A, 1 PCE, white

Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{mm}/25.4 = \text{inch}$
 $\mu\text{m}/25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N}/\text{mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$

$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$
 $\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
 $\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

Available sizes

10044884 WEICON Easy-Mix HT 180 Epoxy Adhesive, 50 ml, black

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weicon.cz

WEICON GmbH & Co. KG
 (Headquarters) Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com

WEICON South East Asia Pte Ltd
 Singapore
 Phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es

WEICON Italia S.r.l.
 Italy
 phone +39 (0) 010 2924 871
 info@weicon.it

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Türkiye
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr