

# Easy-Mix PU-90 Polyurethane Adhesive



**High-strength | extremely fast-curing | high viscosity | pot life approx. 90 seconds**

WEICON Easy-Mix PU-90 Structural Adhesive is a high-strength, extremely fast-curing, highly viscous adhesive, which can be sanded and painted over after approx. 30 minutes. It is weather-resistant, resistant to chemicals and temperature-resistant from -55 °C to +125 °C (-67 to +257 °F). WEICON PU-90 can be used to bond numerous materials such as composite materials, plastics, polyurethane, epoxies, polyester, metals, wood and ceramics to themselves and to each other with high tensile, shear and peel strength. PU-90 can be used in plastic technology, machine construction, model and mould making, metal construction, ship and boat building, carriage and vehicle construction, trade show and exhibition construction and in many other applications.

## Characteristics

Base	polyurethane	
Colour	black	
Minimum shelf life	Humidity < 70 %	18 Mon.

## Processing

Mixing ratio by weight	1:1	
Density of the mixture	1,30-1,35 g/cm <sup>3</sup>	
Gap bridging up to max.	0.1 mm	

## Curing

Pot life	at 20 °C	90 sec.
Handling strength	(35 % strength)	5 min.
Working strength after	(50 % strength)	10 min.
Final strength	(100 % strength)	12 h

## Mechanical properties after curing

Tensile strength	DIN EN ISO 527-2	21 N/mm <sup>2</sup>
Elongation at break (tensile)	DIN EN ISO 527-2	35 %
E-modulus (tensile)	DIN EN ISO 527-2	650-750 N/mm <sup>2</sup>
Hardness (Shore D)		66
Lap shear strength material thicken. 1,5mm DIN EN 1465		
Steel 1.0338 sandblasted		19 N/mm <sup>2</sup>
Stainless steel V2A sandblasted		17 N/mm <sup>2</sup>
Aluminium sandblasted		13 N/mm <sup>2</sup>

## Thermal parameters

Temperature resistance		-55°C to +125°C
Heat deflection resistance	DIN EN ISO 75-2	+65 °C
Temperature conductivity		0,186 mm <sup>2</sup> /s
Thermal conductivity	DIN EN ISO 22007-4	0,283 W/m·K
Heat capacity	DIN EN ISO 22007-4	1.268 J/(g·K)

## Electrical parameters

Resistance		1,90 · 10 <sup>12</sup>
Dielectric strength	DIN EN 60243-1 (20°C)	>22 kV/mm


## Approvals / Guidelines

ISSA Code	75.530.02
IMPA Code	812987

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Tensile strength after storage



## Surface Pre-Treatment

For a flawless adhesive bond, surfaces must be clean and dry (e.g.

clean and degrease with Surface Cleaner). Higher strengths can be achieved by further pre-treatment of the surfaces,

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# Easy-Mix PU-90 Polyurethane Adhesive

such as roughening by blasting or grinding. Some low-energy plastics, especially PTFE and polyolefins etc., can only be bonded after special pre-treatment of the surfaces by e.g. fluorination, low-pressure plasma, corona, flame treatment, or similar.

### Application

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side. The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5 °C and below, no reaction takes place.

### Storage

Store in the unopened original container at a relative humidity of <70% and at a constant room temperature in a dry place. Avoid sources of heat and both direct and indirect sunlight. Once opened, the shelf life is reduced.

### Scope of delivery

Quadro Mixing Nozzle A | Adhesive | Gloves | Primer

### Accessories

- 10005237 Dispenser Easy-Mix D 50, 1 PCE
- 10010887 Processing Spatula short, 1 PCE
- 10005236 Quadro Mixing Nozzle A, 1 PCE, blue
- 10068261 Dosing Tip A Size 0,5 mm, 1 PCE
- 10101999 WEICON Manual Dispenser, 1 x 1:1 | 2:1

### Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
$\text{mm}/25.4 = \text{inch}$	$\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25.4 = \text{mil}$	$\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0.225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

### Available sizes

- 10031972 Easy-Mix PU-90 Polyurethane Adhesive, 50 ml, black

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr