

# Easy-Mix PU Crystal Polyurethane Adhesive

**High-strength | fast-curing | UV-resistant | for transparent and visually appealing adhesive bonds | pot life approx. 120 - 240 seconds**

WEICON Easy-Mix PU Crystal is a crystal clear and colourless two-component polyurethane adhesive for bonding plastics (e.g. polycarbonate) as well as plastics to steel, stainless steel, aluminium, concrete, wood, and glass. The high-strength and fast-curing structural adhesive is sandable and paintable after approx. 30 minutes. It provides excellent adhesion to a variety of materials and is resistant to weathering and many aggressive chemicals. PU is temperature-resistant from -55 °C to +100 °C (-67 °F to +212 °F). Due to its transparent curing, it is particularly suitable for bonding e.g. plastics and glass. It can also be used for structural adhesive bonding, where a coloured adhesive joint would affect the overall appearance of the component. PU Crystal bonds transparent plastics, like Plexiglas and other materials, can be bonded safely in a clean and visually appealing way. PU Crystal can be used in plastic technology, machine construction, model and mould making, metal construction, ship and boat building, carriage and vehicle construction, trade show and exhibition construction, and in many other areas.

## Characteristics

Base	polyurethane
Colour	crystal clear
Minimum shelf life	Humidity < 70 % 12 Mon.

## Processing

Mixing ratio by weight	1:1
Viscosity of the mixture	at +25 °C 6.000-8.000 mPa·s
Density of the mixture	1,13 g/cm³
Gap bridging up to max.	0.1 mm

## Curing

Pot life	at 20 °C 2-4 min.
Handling strength	(35 % strength) 30 min.
Working strength after	(50 % strength) 60 min.
Final strength	(100 % strength) 12 h

## Mechanical properties after curing

Tensile strength	DIN EN ISO 527-2 12 N/mm²
Elongation at break (tensile)	DIN EN ISO 527-2 20 %
E-modulus (tensile)	DIN EN ISO 527-2 240 - 280 N/mm²
Hardness (Shore D)	73
Lap shear strength material thickn. 1.5mm DIN EN 1465	
Steel 1.0338 sandblasted	17 N/mm²
Stainless steel V2A sandblasted	17 N/mm²
Aluminium sandblasted	11 N/mm²
Galvanized steel	12 N/mm²
PC (polycarbonate)	3,2 N/mm²
PMMA	2,3 N/mm²

## Thermal parameters

Temperature resistance	-55°C to +100°C
Tg after curing at room temperature (DSC)	~ 48 °C
Heat deflection resistance	DIN EN ISO 75-2 +50 °C

## Electrical parameters

Dielectric strength	DIN EN 60243-1 (20°C) 20 kV/mm
---------------------	-----------------------------------

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Surface Pre-Treatment

For a flawless adhesive bond, surfaces must be clean and dry (e.g. clean and degrease with Surface Cleaner). Higher strengths can be achieved by further pre-treatment of the surfaces, such as roughening by blasting or grinding. Some low-energy plastics, especially PTFE and polyolefins etc., can only be bonded after special pre-treatment of the surfaces by e.g. fluorination, low-pressure plasma, corona, flame treatment, or similar.

## Processing

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side.

The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5 °C and below, no reaction takes place.

## Storage

Ungeöffnete Gebinde können bei Temperaturen von +18 °C bis +25 °C und einer relativen Luftfeuchtigkeit < 50 % gelagert werden.

## Scope of delivery

Adhesive | Quadro Mixing Nozzle A

## Accessories

10005237	Dispenser Easy-Mix D 50, 1 PCE
10005236	Quadro Mixing Nozzle A, 1 PCE, blue
10010887	Processing Spatula, 1 PCE
10068261	Dosing Tip, 1 PCE

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 10 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# Easy-Mix PU Crystal Polyurethane Adhesive

Polyurethane Systems

## Polyurethanes

### Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
$\text{mm}/25.4 = \text{inch}$	$\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25.4 = \text{mil}$	$\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0.225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

### Available sizes

10058022 Easy-Mix PU Crystal Polyurethane Adhesive, 50 ml, crystal clear

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr