

# WEICON Balancing Putty



## Kneadable balancing compound | fast application without tools

WEICON Balancing Putty is an easy-to-use, cold-curing 2-component epoxy resin system. The resin putty is used especially for balancing armatures for electric motors. Compared to machining processes such as drilling or milling, this type of balancing has several advantages. No tools are required for the processing of the balancing putty. And no work is required on the armature core. This results in a quality improvement in terms of motor noise and efficiency. The use of putty saves time, as e.g. deburring the balanced areas is not necessary. Armatures, which were single-plane balanced by machining, can be two-plane balanced with the Balancing Putty without requiring additional time. No metal chips are created, which can get caught in the winding and cause damage. The potential risk of accidents during drilling and/or milling is eliminated. For example, the Balancing Putty is not shaken off in the test run (in uncured condition) during the balancing process at 3000 rpm (diameter of the armature 40mm).

### Characteristics

Base	Epoxy
Filler	mineral
Texture	pasty
Minimum shelf life	at room temperature 36 mon.

### Processing

Processing temperature	+15 °C to +40 °C
Cure temperature	+6 °C to +40 °C
Mixing ratio by weight	100:86
Mixing ratio by volume	100:79
Density of the mixture	2,5 g/cm <sup>3</sup>
Consumption	Layer thickness 1.0 mm 2.5 kg/m <sup>2</sup>

### Curing

Pot life	at 20 °C	60 min.
Working strength after		10 h
Final strength	(100 % strength)	16 h
Shrinkage		0,05 %

### Mechanical properties after curing

Tensile strength		30 MPa
E-modulus (tensile)	DIN EN ISO 527-2	4.000 - 6.000 MPa
Compressive strength	DIN EN ISO 604	80 MPa
Hardness (Shore D)		90

### Thermal parameters

Temperature resistance		-40 °C to +130 °C (briefly up to +300 °C)
Tg after curing at room temperature		~ 80 °C
Heat deflection resistance	DIN EN ISO 75-2	+ 95 °C
Thermal expansion coefficient	ISO 11359	40 · 10 <sup>-6</sup> 1/m·K
Thermal conductivity		0,6 W/m·K

### Electrical parameters

Resistance		1,0 · 10 <sup>14</sup> Ω·m
------------	--	----------------------------

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Surface Pre-Treatment

Surfaces must be grease-free and clean, roughen if necessary.

### Processing

Mixing ratio by volume 1:1; by weight 100 parts resin (blue): 86 parts hardener (yellow). Mix both components until the mixture has taken on a uniform green colour. In case of blue or yellow inclusions, the mixing process was insufficient.

### Storage

Store WEICON Plastic-Metal at room temperature in a dry place. Unopened containers can be stored at temperatures of +18°C to +25 °C. Opened containers must be used up within 6 months.

### Scope of delivery

Instructions for use | Resin & Hardener

### Conversion table

(°C x 1.8) + 32 = °F  
mm/25.4 = inch  
µm/25.4 = mil  
N x 0.225 = lb  
N/mm<sup>2</sup> x 145 = psi  
MPa x 145 = psi

Nm x 8.851 = lb·in  
Nm x 0.738 = lb·ft  
Nm x 141.62 = oz·in  
mPa·s = cP  
N/cm x 0.571 = lb/in  
kV/mm x 25.4 = V/mil

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# WEICON Balancing Putty

## Available sizes

10000129	WEICON Balancing Putty, 400 g
10000113	WEICON Balancing Putty, 1 kg
10000114	WEICON Balancing Putty, 5 kg

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr