

# Repair Stick Plastic



## plastic-filled | drinking water approval

WEICON Repair Stick Plastic was developed specifically for long-lasting repairs of plastic components and composite materials such as window and door frames, panelling and bumper bars. It remains elastic permanently. It is suitable for bonding metal pieces, such as pipes and pipe bends, fittings and flanges, water tanks, pumps and housings.

The Repair Stick can be used in window construction, container and apparatus construction, in the food, cosmetics and pharmaceutical industries and in many other areas.

### Characteristics

Base	epoxy
Filler	mineral
Texture	modelling compound
Colour	white-blue
Minimum shelf life	at room temperature 24 mon.

### Processing

Processing temperature	+15 °C (59 °F) to +40 °C (104 °F)
Component temperature	>3 °C above dew point
Cure temperature	+6 °C to +40 °C (+42 °F to +104 °F)
Relative air humidity	< 85 %
Mixing ratio by weight	1:1
Density of the mixture	1,6 g/cm <sup>3</sup>
Gap bridging up to max.	15 mm

### Curing

Pot life	at 20 °C, 10 g batch	15 min.
Handling strength		40 min.
Working strength after	(80 % strength)	3 h
Final strength	(100 % strength)	24 h
Shrinkage		<1,0 %

### Mechanical properties after curing

Compressive strength	DIN EN ISO 604	55 MPa
Hardness (Shore D)	DIN ISO 7619	65±3
Adhesive strength	DIN EN ISO 4624	3 MPa

### Thermal parameters

Temperature resistance	from -50 °C (-58 °F) to +120 °C (248 °F), briefly up to +150 °C (302 °F)
Thermal conductivity	DIN EN ISO 22007-4 0,4 W/m·K


### Electrical parameters

Resistance	DIN EN 62631-3-1	~ 5·10 <sup>11</sup> Ω·m
Electrical resistance	ASTM D 257	5 Ω·cm
Dielectric strength		3,0 kV/mm
Magnetic		no

### Approvals / Guidelines

NSF	NSF/ANSI Standard 61
ISSA Code	75.530.08/09
IMPA Code	812973/74

### Increase in strength



### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Surface Pre-Treatment

The successful application of WEICON Repair Sticks depends on the careful preparation of the surfaces. Dust, dirt, oil, grease, residues, rust, moisture or dampness have a negative impact on adhesion. Best results are achieved with application on clean, solid and thoroughly roughened surfaces.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# Repair Stick Plastic

Surfaces must be clean, dry and free of grease. Almost all surface contaminants, such as old paint residues, oil, grease, dust and dirt, can be removed with WEICON Surface Cleaner or WEICON Sealant and Adhesive Remover. On surfaces that are extremely dirty or smooth, the adhesion can be improved by mechanical roughening with coarse abrasives.

After mechanical pre-treatment, the surface should be cleaned again with WEICON Surface Cleaner.

## Application

We recommend an ambient temperature of 20°C (68°F) with less than 85% relative humidity for processing. Only prepare a batch as large as can be processed within the pot life. The pot life and curing time indicated refer to a material batch of 10 g at room temperature. With larger batch sizes or higher processing temperatures, the curing process is faster due to the typical reaction heat of epoxy resins (exothermic reaction).

Twist off or cut off the required amount from the Repair Stick. The components should be mixed together until a homogeneous mixture and colour is achieved. If necessary, the putty can be warmed to room temperature to facilitate mixing.

Work the thoroughly kneaded Repair Stick into the cracks and holes to be filled, and wipe off any excess material before it hardens. To achieve a smooth surface, the material can be smoothed with water or a damp cloth before it hardens. The curing process can be accelerated by heating the Repair Stick or by applying it to a warm surface. After approx. 3 hours at room temperature, the repaired area is mechanically stable and can be threaded, drilled or sanded.

WEICON Repair Sticks can bridge a gap of up to 15 mm per application.



## Curing

The specified final hardness refers to curing at 20°C (68°F). At lower temperatures, the curing process can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with heat pockets, hot air or fan heaters. Higher temperatures also reduce the pot life and curing time.

The following rule of thumb applies: each increase by +10°C (50°F) above room temperature 20°C (68°F) will decrease the pot life and curing time by half. Temperatures below +16°C (61°F) increase the pot life and curing time, until at approx. +5°C (41°F) and below, almost no reaction will take place at all.

## Storage

Store in unopened original container at constant room temperature in a dry place. Avoid sources of heat and both direct and indirect sunlight. Once opened, the shelf life is reduced.

## Scope of delivery

Adhesive

## Accessories

- 10024313 Surface Cleaner, 400 ml, transparent
- 10026705 Sealant and Adhesive Remover, 400 ml, pink

## Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$	$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
$\text{mm}/25.4 = \text{inch}$	$\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
$\mu\text{m}/25.4 = \text{mil}$	$\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
$\text{N} \times 0.225 = \text{lb}$	$\text{mPa}\cdot\text{s} = \text{cP}$
$\text{N}/\text{mm}^2 \times 145 = \text{psi}$	$\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
$\text{MPa} \times 145 = \text{psi}$	$\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

## Available sizes

- 10017301 Repair Stick Plastic, 57 g, white-blue
- 10017334 Repair Stick Plastic, 115 g, white-blue

To the product detail page:



Note  
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# Repair Stick Plastic

## Chemical resistance after curing\* (Excerpt)

1,4-Dioxane	-	Glycol	+
Exhaust fumes	+	Uric acid	-
Adipic acid	-	Impregnating oils	+
aliphatic hydrocarbons	+	Iodides (K, Na etc.)	-
Formic acid >10 % (methanoic acid)	-	Potassium carbonate	+
Ammonia anhydrous 25%	-	Potassium hydroxide 0-20 % (caustic potash)	+
Aniline	-	Milk of lime	+
aromatic hydrocarbons	+	Cresol	-
Barium hydroxide	+	Magnesium hydroxide	+
Benzoic acid	-	Maleic acid (cis-ethylenedicarboxylic acid)	-
Benzyl alcohol	-	Methanol (methyl alcohol ) <85 %	o
Benzyl chloride	-	Methylene chloride	-
Boric acid	-	Mineral oil	+
Bromides	-	Naphthalene	+
Butadiene (1,3-)	-	Sodium bicarbonate (sodium hydrogen carbonate)	+
Butyric acid	-	Sodium carbonate (soda)	+
Butyl acetate	o	Sodium chloride (table salt)	+
Butyl alcohol	o	Nitrates	-
Calcium hydroxide (slaked lime)	+	Nitrobenzene	-
Chloroanilines	-	Oils, vegetable and animal	+
Chloroform (trichlormethane)	-	Oxalic acid <25 % (ethanedioic acid)	o
Chlorosulphuric acid (wet and dry)	-	Perchloraethylene	-
Chlorosilanes	-	Kerosene	+
Chlorinated water (swimming pool concentration)	-	Phenol	-
Chromates (K, Na, etc.)	-	Phosphoric acid <50%	+
Chromic acid	-	Phthalic acid, phthalic anhydride	-
Cyanides (K, Na etc.)	-	Nitric acid <5%	-
Cyclohexanone	-	Sulphur dioxide (wet and dry)	-
Diethyl ether	+	Carbon disulphide	-
Mineral oil and mineral oil products	+	Sulphuric acid <5%	+
Acetic acid diluted <5%	o	Soap solution	+
Ethanol <85 % (ethyl alcohol)	o	Turpentine	+
Greases, oils and waxes	+	Carbon tetrachloride (tetrachloromethane)	-
Hydrofluoric acid	-	Tetralin (tetrahydronaphthalene)	-
Tannic acid diluted <7%	o	Trichloraethylene	-
Glycerin (trihydroxipropane)	+	Hydrogen peroxide <30 % (hydrogen superoxide)	o

+ = resistant 0 = for a limited time - = not resistant \*The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

**Note**

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr