

# Repair Stick Concrete



## fast-curing | ceramic-filled

Especially for the quick repair and reconditioning of all concrete, stone and ceramic surfaces.

Fills and seals cracks and defects on masonry, stone, concrete and ceramic tiles and on bricks, borders, kerbstones, statues, tombstones and ornaments. It can also be used for the reinforcement of pegs, screws and anchors in outdoor and indoor areas.

The WEICON Repair Stick Concrete can be used in the construction industry, in gardening and landscaping, and in many other applications.

### Characteristics

|                    |                     |         |
|--------------------|---------------------|---------|
| Base               | epoxy               |         |
| Filler             | ceramic             |         |
| Texture            | modelling compound  |         |
| Colour             | concrete grey       |         |
| Minimum shelf life | at room temperature | 24 mon. |

### Processing

|                         |                                     |  |
|-------------------------|-------------------------------------|--|
| Processing temperature  | +15 °C (59 °F) to +40 °C (104 °F)   |  |
| Component temperature   | >3 °C above dew point               |  |
| Cure temperature        | +6 °C to +40 °C (+42 °F to +104 °F) |  |
| Relative air humidity   | < 85 %                              |  |
| Mixing ratio by weight  | 1:1                                 |  |
| Density of the mixture  | 1,9 g/cm <sup>3</sup>               |  |
| Gap bridging up to max. | 15 mm                               |  |

### Curing

|                        |                      |          |
|------------------------|----------------------|----------|
| Pot life               | at 20 °C, 10 g batch | ~ 5 min. |
| Handling strength      | (35 % strength)      | 15 min.  |
| Working strength after | (80 % strength)      | 60 min.  |
| Final strength         | (100 % strength)     | 24 h     |
| Shrinkage              |                      | <1,0 %   |

### Mechanical properties after curing

|                      |                 |        |
|----------------------|-----------------|--------|
| Compressive strength | DIN EN ISO 604  | 55 MPa |
| Hardness (Shore D)   | DIN ISO 7619    | 80±3   |
| Adhesive strength    | DIN EN ISO 4624 | 6 MPa  |

### Thermal parameters

|                        |  |           |
|------------------------|--|-----------|
| Temperature resistance | from -50 °C (-58 °F) to +120 °C (248 °F), briefly up to +150 °C (302 °F) |           |
| Thermal conductivity   | DIN EN ISO 22007-4   | 0,5 W/m·K |


### Electrical parameters

|                       |                  |                          |
|-----------------------|------------------|--------------------------|
| Resistance            | DIN EN 62631-3-1 | ~ 5·10 <sup>11</sup> Ω·m |
| Electrical resistance | ASTM D 257       | 5 Ω·cm                   |
| Dielectric strength   |                  | 3,0 kV/mm                |
| Magnetic              |                  | no                       |

### Approvals / Guidelines

|           |              |
|-----------|--------------|
| ISSA Code | 75.530.15/16 |
| IMPA Code | 812967/68    |

### Increase in strength



### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Surface Pre-Treatment

The successful application of WEICON Repair Sticks depends on the careful preparation of the surfaces. Dust, dirt, oil, grease, residues, rust, moisture or dampness have a negative impact on adhesion. Best results are achieved with application on clean, solid and thoroughly roughened surfaces.

Surfaces must be clean, dry and free of grease. Almost all surface contaminants, such as old paint residues, oil, grease, dust and dirt, can be removed with WEICON Surface Cleaner or WEICON Sealant and Adhesive Remover. On surfaces that are extremely dirty or smooth, the adhesion can be improved by mechanical roughening with coarse abrasives.

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# Repair Stick Concrete

After mechanical pre-treatment, the surface should be cleaned again with WEICON Surface Cleaner.

## Application

We recommend an ambient temperature of 20°C (68°F) with less than 85% relative humidity for processing. Only prepare a batch as large as can be processed within the pot life. The pot life and curing time indicated refer to a material batch of 10 g at room temperature. With larger batch sizes or higher processing temperatures, the curing process is faster due to the typical reaction heat of epoxy resins (exothermic reaction).

Twist off or cut off the required amount from the Repair Stick. The components should be mixed together until a homogeneous mixture and colour is achieved. If necessary, the putty can be warmed to room temperature to facilitate mixing.

Work the thoroughly kneaded Repair Stick into the cracks and holes to be filled, and wipe off any excess material before it hardens. To achieve a smooth surface, the material can be smoothed with water or a damp cloth before it hardens. The curing process can be accelerated by heating the Repair Stick or by applying it to a warm surface. After approx. 60 minutes at room temperature, the repaired area is mechanically stable and can be threaded, drilled or sanded.

WEICON Repair Sticks can bridge a gap of up to 15 mm per application.



## Curing

The specified final hardness refers to curing at 20°C (68°F). At lower temperatures, the curing process can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with heat pockets, hot air or fan heaters. Higher temperatures also reduce the pot life and curing time.

The following rule of thumb applies: each increase by +10°C (50°F) above room temperature 20°C (68°F) will decrease the pot life and curing time by half. Temperatures below +16°C (61°F) increase the pot life and curing time, until at approx. +5°C (41°F) and below, almost no reaction will take place at all.

## Storage

Store in unopened original container at constant room temperature in a dry place. Avoid sources of heat and both direct and indirect sunlight. Once opened, the shelf life is reduced.

## Scope of delivery

Adhesive

## Accessories

- 10024313 Surface Cleaner, 400 ml, transparent
- 10026705 Sealant and Adhesive Remover, 400 ml, pink

## Conversion table

|   |   |
|---|---|
| $(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$ | $\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$      |
| $\text{mm}/25.4 = \text{inch}$                          | $\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$      |
| $\mu\text{m}/25.4 = \text{mil}$                         | $\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$     |
| $\text{N} \times 0.225 = \text{lb}$                     | $\text{mPa}\cdot\text{s} = \text{cP}$                   |
| $\text{N}/\text{mm}^2 \times 145 = \text{psi}$          | $\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$ |
| $\text{MPa} \times 145 = \text{psi}$                    | $\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$ |

## Available sizes

- 10025685 Repair Stick Concrete, 57 g, concrete grey
- 10025687 Repair Stick Concrete, 115 g, concrete grey

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# Repair Stick Concrete

## Chemical resistance after curing\* (Excerpt)

|   |   |  |   |
|---|---|--|---|
| 1,4-Dioxane                                     | - | Glycol   | + |
| Exhaust fumes                                   | + | Uric acid                                      | - |
| Adipic acid                                     | - | Impregnating oils                              | + |
| aliphatic hydrocarbons                          | + | Iodides (K, Na etc.)                           | - |
| Formic acid >10 % (methanoic acid)              | - | Potassium carbonate                            | + |
| Ammonia anhydrous 25%                           | - | Potassium hydroxide 0-20 % (caustic potash)    | + |
| Aniline   | - | Milk of lime                                   | + |
| aromatic hydrocarbons                           | + | Cresol   | - |
| Barium hydroxide                                | + | Magnesium hydroxide                            | + |
| Benzoic acid                                    | - | Maleic acid (cis-ethylenedicarboxylic acid)    | - |
| Benzyl alcohol                                  | - | Methanol (methyl alcohol ) <85 %               | o |
| Benzyl chloride                                 | - | Methylene chloride                             | - |
| Boric acid                                      | - | Mineral oil                                    | + |
| Bromides  | - | Naphthalene                                    | + |
| Butadiene (1,3-)                                | - | Sodium bicarbonate (sodium hydrogen carbonate) | + |
| Butyric acid                                    | - | Sodium carbonate (soda)                        | + |
| Butyl acetate                                   | o | Sodium chloride (table salt)                   | + |
| Butyl alcohol                                   | o | Nitrates                                       | - |
| Calcium hydroxide (slaked lime)                 | + | Nitrobenzene                                   | - |
| Chloroanilines                                  | - | Oils, vegetable and animal                     | + |
| Chloroform (trichlormethane)                    | - | Oxalic acid <25 % (ethanedioic acid)           | o |
| Chlorosulphuric acid (wet and dry)              | - | Perchloraethylene                              | - |
| Chlorosilanes                                   | - | Kerosene                                       | + |
| Chlorinated water (swimming pool concentration) | - | Phenol   | - |
| Chromates (K, Na, etc.)                         | - | Phosphoric acid <50%                           | + |
| Chromic acid                                    | - | Phthalic acid, phthalic anhydride              | - |
| Cyanides (K, Na etc.)                           | - | Nitric acid <5%                                | - |
| Cyclohexanone                                   | - | Sulphur dioxide (wet and dry)                  | - |
| Diethyl ether                                   | + | Carbon disulphide                              | - |
| Mineral oil and mineral oil products            | + | Sulphuric acid <5%                             | + |
| Acetic acid diluted <5%                         | o | Soap solution                                  | + |
| Ethanol <85 % (ethyl alcohol)                   | o | Turpentine                                     | + |
| Greases, oils and waxes                         | + | Carbon tetrachloride (tetrachloromethane)      | - |
| Hydrofluoric acid                               | - | Tetralin (tetrahydronaphthalene)               | - |
| Tannic acid diluted <7%                         | o | Trichloraethylene                              | - |
| Glycerin (trihydroxipropane)                    | + | Hydrogen peroxide <30 % (hydrogen superoxide)  | o |

+ = resistant 0 = for a limited time - = not resistant \*The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

**Note**

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Colombia S.A.S  
Colombia  
Phone: +57 314 793 86 06  
Email: info@weicon.co

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.L.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr