

# RK-1500 Structural Acrylic Adhesive



## Liquid | strong | fast-curing

The structural acrylic adhesive WEICON RK-1500 is particularly suitable for bonding glass, metal and ceramics. Together with an activator, the adhesive forms a 2C-system that is processed in the no-mix procedure. The elimination of mixing processes simplifies the application considerably. The transparent adhesive has a high impact, peel and shear strength. Thanks to its low viscosity, RK-1500 is particularly suitable for use on large surfaces. RK-1500 can be used in mechanical and apparatus engineering, vehicle construction, tool and mould making, in the building and furniture industry, and in many other industrial applications.

## Characteristics

Base	methyl methacrylate
Texture	flowable
Colour	pale yellow, transparent
Minimum shelf life	at room temperature
Minimum shelf life	12 mon.
Minimum shelf life	from +2 °C to +7 °C
24 Mon.	

## Processing

Processing procedure	No-Mix
Processing temperature	+10°C to +40°C
Curing temperature	> +18 °C
Cure temperature	+18
Viscosity	4.500 mPa·s
Density of the mixture	1,00 g/cm³
Gap bridging up to max.	0.4 mm

## Curing

Handling strength	(35 % strength)	5 min.
Working strength after	(50 % strength)	8 min.
Final strength	(100 % strength)	24 h

## Mechanical properties after curing

Lap shear strength material thickn. 1,5mm DIN EN 1465	
Steel 1.0338 sandblasted	25 N/mm²
Stainless steel V2A sandblasted	30 N/mm²
Aluminium sandblasted	20 N/mm²
PVC-rigid roughened	11 N/mm²
CFRP	27 N/mm²
ABS	6 N/mm²
PC (polycarbonate)	10 N/mm²
GFRP	20 N/mm²
PMMA	8 N/mm²
Polyamide 6.6	3 N/mm²

## Thermal parameters

Temperature resistance	-50 °C to +130 °C, briefly up to +180 °C
------------------------	--

## Approvals / Guidelines

ISSA Code	75.629.53
IMPA Code	812992
MIL-Spec	complies with MIL-PRF-23400

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Surface Pre-Treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner). Higher strengths can be achieved by further pre-treatment of the surfaces, such as roughening by blasting or grinding. Some plastics, especially polyamides, PTFE, polyolefines etc., can only be bonded after special pre-treatment of the surfaces by e.g. fluorination, low-pressure plasma, corona, flame treatment, or similar.

## Application

**Processing the RK Activator:** Depending on the size of the bonding gap, the RK Activator is applied to one or both sides of the bonding surfaces (brush, spray, dip). For adhesive gaps up to max. 0.4 mm, a single-sided application is sufficient; for adhesive gaps up to max. 0.8 mm and/or rough, porous as well as passive surfaces (chrome, nickel, etc.), a double-sided application is required. For smooth plastic and metal surfaces approx. 30 g/m², for rough and porous surfaces up to 150 g/m² activator are required. The flash-off time is at least 5 minutes at room temperature (+20°C). A significant advantage over other adhesive systems is that the coated workpieces can be stored at room temperature (+20°C) for up to 30 days without the effectiveness decreasing. **Processing of the RK Adhesive:** The adhesive is only applied on to side and usually to the surface not coated with activator. The bonding gap can be up to 0.80 mm (only with activator applied to both sides). Adhesive joints with a thickness of 0.15 mm to 0.25 mm generally have the highest tensile shear strength. For smooth plastic and metal surfaces approx. 180 g/m², for rough and porous surfaces up to 300 g/m² activator are

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# RK-1500 Structural Acrylic Adhesive

required. Processing temperature: The processing should be done at room temperature (+20°C). Higher temperatures e.g. +40°C shorten the positioning and curing times by approx. 30%; low temperatures around +10°C increase the respective times by approx. 50%, until from +5°C almost no reaction takes place.

## Storage

RK adhesive and RK activator:

WEICON RK construction adhesives should be stored in a dry place at a constant room temperature. Unopened containers can be stored at temperatures from +18 °C to +25 °C. Protect from direct sunlight. If the storage temperature exceeds +40 °C and the air humidity is high, the shelf life is reduced to 6 months.

## Scope of delivery

RK1500 mass | Activator | Wooden spatula | Tip for RK1300/1500

## Accessories

10010887 Processing Spatula, 1 PCE  
10022562 Processing Spatula, 1 PCE  
10032350 Primer Applicator, 1 PCE

## Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	Nm x 0.738 = lb·ft
µm/25.4 = mil	Nm x 141.62 = oz·in
N x 0.225 = lb	mPa·s = cP
N/mm² x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

## Available sizes

10008905 RK-1500 Structural Acrylic Adhesive, 60 g, pale yellow, transparent  
10100180 RK-1500 Structural Acrylic Adhesive, 6 kg, pale yellow, transparent  
10016249 RK-1500 Structural Acrylic Adhesive, 0,31 kg, pale yellow, transparent  
10002622 RK-1500 Structural Acrylic Adhesive, 1 kg, pale yellow, transparent

To the product detail page:



## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr