

WEICONLOCK® AN 305-10 Flange sealing



Gasketing of flanges | high-temperature-resistant | BAM

- high viscosity
- high strength
- hard to disassemble

Technical Data

Colour	orange	
Fluorescent	yes	
Viscosity	+25 °C Brookfield	70.000 - 300.000 ht mPa·s
Gap bridging up to max.	0,5 mm	
Breakaway torque	18 - 25 Nm	
Prevail torque	15 - 25 Nm	
Shear strength Nmm ² (DIN 54452)	5 - 10 N/mm ²	
Handling strength	15 - 30 min.	
Final strength	(100 % strength)	6-12 h
Temperature resistance	-60°C to +200°C	
Minimum shelf life	at room temperature	24 mon.
Compressive strength (free cutting steel / grub screw = 8.8)		
M 3x6	max.	1500 bar
M 4x6	max.	1500 bar
M 5x8	max.	1500 bar
M 6x10	max.	1200 bar
M 8x12	max.	800 bar
M 10x16	max.	500 bar

Approvals / Guidelines

AGA	AS 4623-2008
-----	--------------

Surface Pre-Treatment

Clean surfaces to be sealed.

Application

WEICONLOCK is applied evenly straight from the Pen/the cartridge; avoid direct contact between dosing tip/metal. Apply continuous bead to one flange side, then assemble parts quickly and screw tight. For sealing applications (pipe fittings), apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

Store WEICONLOCK in the unopened original container at room temperature. Avoid sources of heat and direct sunlight. The air inside the packaging helps maintain storage stability.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

- 10021433 Activator F, 200 ml, green
- 10001256 Dosing Tip L Size 1, 1 PCE

Available sizes

- 10019937 WEICONLOCK® AN 305-10 Flange sealing, 50 ml, orange
- 10019995 WEICONLOCK® AN 305-10 Flange sealing, 200 ml, orange
- 10000511 WEICONLOCK® AN 305-10 Flange sealing, 250 ml, orange
- 10002596 WEICONLOCK® AN 305-10 Flange sealing, 300 ml, orange

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr