

# Primer M 100



## for non-absorbent surfaces

For pre-treating non-absorbent metal surfaces (aluminium, steel, stainless steel, brass, copper, zinc, tinplate), plastics (ABS, rigid PVC, PA 6.6, FRP, SMC, PUR), lacquered surfaces, enamel, ceramics, and glass.

### Characteristics

Base	Synthetic resin, containing solvent
Colour	colourless, transparent
Minimum shelf life	at room temperature 12 mon.

### Processing

Adhesive application at the latest after	24 h
Density	0,79 g/cm <sup>3</sup>
Consumption	20 - 40 ml/m <sup>2</sup>

### Approvals / Guidelines

IMPA Code	812982
-----------	--------

## Surface Pre-Treatment

The surfaces to be treated need to be dry, clean and free of dust and grease (e.g. WEICON Surface Cleaner).

## Application

Shake WEICON Primer well before use and apply a thin layer with a clean cloth. Observe the flash-off times: Primer M 100 at least. 10 min., max. 24 h.

Primer K 200 at least. 10 min., max. 24 h.

Primer S 300 at least. 60 min., max. 4 h.

Primer P 400 at least. 10 min., max. 1 h.

Primer E 500 at least. 60 min., max. 8 h.

The subsequent adhesive bonding should be carried out within the specified period of time. Allow sufficient flash-off time. In case of longer storage times or repeated contamination in the meantime, clean and apply primer to the adherends again. For unfamiliar materials, suitability and compatibility tests are indispensable.

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Accessories

MA10059417  
MA10065455  
MA10068373  
MA10032350

## Available sizes

10023566 Primer M 100, 250 ml, colourless, transparent  
10060606 Primer M 100, 25 ml, colourless, transparent

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr