

# WEICON Anti-Stick



**anti-stick effect | increased efficiency | sprayable**

WEICON Anti-Stick is a liquid, grey 2-component epoxy resin system with mineral fillers for the protection of heavily stressed surfaces against aggressive chemicals and corrosion. It was specially developed for application with low-pressure equipment. In addition to the mineral fillers, Anti-Stick contains special additives that create an anti-stick effect and thus prevent flour, dust or suspended particles, for example, from sticking.

The epoxy resin system has good chemical and thermal resistance up to +120 °C. It is free from solvents and cures with virtually no shrinkage.

A coating with WEICON Anti-Stick, which gives surfaces a very smooth finish, increases the flow speed of liquids and thus increases the efficiency of pumps, pipes, valves, etc. by 5 % to 20 %.

Anti-Stick is applied directly to the parts by sandblasting after thorough preparation of the substrate. The coating adheres very well to a wide variety of surfaces and is suitable for many different parts such as plain bearings, chutes, funnels and pipes as well as for coating castings and valves.

The system can be used in mechanical and plant engineering, in apparatus engineering, in the paper industry, in the bulk goods industry, in exhaust gas systems, in mining, in open-cast mining, in chemical plants and in many other areas of industrial production. In any case, preliminary tests under practical conditions are recommended; especially if the parts are additionally exposed to increased temperature or mechanical stress.

WEICON Anti-Stick is suitable on its own or in combination with one of the other WEICON plastic metal types for a system build-up as an anti-stick coating.

## Characteristics

Base	epoxy
Filler	mineral
Texture	liquid
Colour	grey
Minimum shelf life	at room temperature 24 mon.

## Processing

Processing temperature	+15 °C to +40 °C
Component temperature	>3 °C above dew point
Relative air humidity	max. 85%
Mixing ratio by weight	100 : 45
Mixing ratio by volume	100 : 61
Viscosity of the mixture	at +25 °C 15.000-20.000 mPa·s
Density of the mixture	1,5 g/cm <sup>3</sup>
Consumption	Layer thickness 1.0 mm 1,5 kg/m <sup>2</sup>
Max. layer thickness	per step 10 mm

## Curing

Pot life	at 20 °C, 500 g batch	~ 30 min.
Additional layer after	(35 % strength)	5 h
Working strength after	(80 % strength)	8 h
Final strength	(100 % strength)	24 h
Shrinkage		0,22 %

## Mechanical properties after curing

- Measured after curing at		24 h RT + 24 h 60 °C
Tensile strength	DIN EN ISO 527-2	54 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	1,0 %
E-modulus (tensile)		4.500-5.000 MPa
Compressive strength	DIN EN ISO 604	118 MPa
Bending strength	DIN EN ISO 178	76 MPa
Hardness (Shore D)	DIN ISO 7619	87±3
Adhesive strength	DIN EN ISO 4624	22,2 MPa
Taber Test	DIN ISO 9352 (H18, 1 kg, 1000 rotations)	0,5 g / 0,3 cm <sup>3</sup>
Lap shear strength material thicken. 1,5mm DIN EN 1465		
	Steel 1.0338 sandblasted	17 MPa
	Stainless steel V2A sandblasted	19 MPa
	Aluminium sandblasted	10 MPa
	Galvanized steel	6 MPa

## Thermal parameters

Temperature resistance		-35 °C to +120 °C
Tg after curing at room temperature	(DSC)	56 °C
Tg after tempering (at 120°C)	(DSC)	60 °C
Heat deflection resistance	DIN EN ISO 75-2	65 °C
Thermal conductivity	DIN EN ISO 22007-4	0,684 W/m·K
Heat capacity	DIN EN ISO 22007-4	0,1255 J/(g·K)

## Electrical parameters

Resistance	DIN EN 62631-3-1	7,17 · 10 <sup>-14</sup> Ω·m
Magnetic		no

### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 10 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

# WEICON Anti-Stick

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Surface Pre-Treatment

The successful application of WEICON Anti-Stick depends on the careful pre-treatment of the surfaces. This is the most important factor for ensuring overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on adhesive strength. Therefore, before processing WEICON Anti-Stick, the following points must be observed: the areas to be bonded or repaired must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S. Smooth and exceptionally soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by abrasive blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 1/2 - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75-100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. Multi-use abrasive media (slag, glass, quartz) but also ice blasting will have a negative effect on the surface quality. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON Anti-Stick, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6). The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m<sup>2</sup>. Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture. After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied. Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500. After the surface pre-treatment, WEICON Anti-Stick should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

## Mixing

First, stir the resin. Then mix the resin and hardener together thoroughly and bubble-free for at least four minutes at 20°C (68°F). The included processing spatula or a mechanical mixer, such as a mortar stirrer, can be used for this purpose. With mechanical mixers, a low speed of max. 500 rpm should be used. The components should be stirred until a homogeneous mixture is achieved. The mixing ratio of the two components must be strictly observed, as otherwise strongly deviating


physical values will result (max. deviation +/- 2 %). Only prepare a batch as large as can be processed within the pot life of 30 minutes. The indicated pot life time refers to a material batch of 500 g and 20°C material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins.

## Application

For processing, we recommend an ambient temperature of 20°C (68 °F) at less than 85% relative humidity. For a thin pre-coat, work WEICON Anti-Stick thoroughly into the surface in crosswise layers using the Contour Spatula Flexy to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, further applications can be carried out straight away, until the desired layer thickness is reached. Make sure that the epoxy resin is applied evenly and without air bubbles. To fill large gaps or holes, fibreglass, expanded metal or other mechanical fixing materials should be used. Finally, the surface can be smoothed easily with the help of a PE film and a rubber roller.

## Curing

Final hardness is reached after 24 hours at 20°C at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40°C (104°F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time. The following rule of thumb applies: each increase by +10°C (50°F) above room temperature (20°C/68°F) will decrease the curing time by half. Temperatures below 16°C (61°F) increase the curing time, until at approx. 5°C (41°F) and below, almost no reaction will take place.



## Storage

WEICON Epoxy Resin Systems should be stored in a dry place at room temperature. Unopened containers can be

Note  
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 10 2924 571  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

## WEICON Anti-Stick

stored at temperatures from +18 °C to +28 °C. Opened containers must be used up within 6 months.

### Scope of delivery

Processing Spatula | Instructions for use | Gloves | Resin & Hardener

### Accessories

- 1000147 Cleaner Spray S, 500 ml, transparent
- 1000347 Cleaner S, 5 L, colourless, transparent
- 10024313 Surface Cleaner, 400 ml, transparent
- 10025288 Surface Cleaner, 5 L, transparent
- 10026647 Mould Release Agent Liquid F 1000, 250 ml, white, milky
- 10026712 Mould Release Agent Wax P 500, 150 g
- 10053995 Repair Stick Multi-Purpose, 115 g, vintage white
- 10000913 Glass Fibre Cloth Tape, 1 PCE, white
- 10010887 Processing Spatula short, 1 PCE
- 10022562 Processing Spatula long, 1 PCE
- 10059417 Brush 35 short, flat, Plastic Metal, 1 PCE
- 10001978 Stirrer Stainless Steel, 1 PCE
- 10016002 Pump Dispenser WPS 1500, 1 PCE
- 10000441 Cartridge Gun, 1 PCE
- 10002034 Empty cartridge, 1 PCE
- 10039667 Cable Scissors No. 35, 1 PCE
- 10045523 Processing Kit, 1 PCE

### Recommended equipment

- Angle grinder
- Blast machine
- Heat pocket
- Hot or fan heater
- Smoothing trowel, spatula
- PE film 0.2 mm
- Fabric tape
- Brush
- Foam roller
- Rubber roller
- Lint-free cloth

### Conversion table

- (°C x 1.8) + 32 = °F
- Nm x 8.851 = lb·in
- mm/25.4 = inch
- Nm x 0.738 = lb·ft
- µm/25.4 = mil
- Nm x 141.62 = oz·in
- N x 0.225 = lb
- mPa·s = cP
- N/mm<sup>2</sup> x 145 = psi
- N/cm x 0.571 = lb/in
- MPa x 145 = psi
- kV/mm x 25.4 = V/mil

### Available sizes

- 10062938 WEICON Anti-Stick, 0,2 kg, grey
- 10062940 WEICON Anti-Stick, 0,5 kg, grey
- 10062941 WEICON Anti-Stick, 2 kg, grey

	WEICON A	WEICON B	WEICON BR	WEICON C	WEICON F	WEICON F2	WEICON HB 300	WEICON HT 111	WEICON SF	WEICON ST	WEICON TI	WEICON UW	WEICON WR2	WEICON HP	WEICON Fire Safe	WEICON Anti-Static	WEICON Food Grade	WEICON Anti-Stick	WEICON Ceramic BL	WEICON GL	WEICON GL-S	WEICON Ceramic W	WEICON Ceramic HC 220	WEICON WP	WEICON WR	WEICON CBC
Repair and moulding	x	x	x	x	x	x	x	x	x	x	x	x	x													
Adhesive				x	x		x	x		x				x	x											
Wear, erosion and corrosion protection – abrasion-resistant coating																x	x	x	x	x	x	x	x	x		
Casting, relining and gap compensation – casting and injecting potting compound	x					x							x												x	x

To the product detail page:



#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr

## WEICON Anti-Stick

### Chemical resistance after curing\* (Excerpt)

Exhaust fumes	+	Potassium carbonate	+
Acetone	o	Potassium hydroxide 0-20 % (caustic potash)	+
Ethyl ether	+	Milk of lime	+
Ethyl alcohol	o	Carbolic acid	-
Ethylbenzene	-	Creosote oil	-
Alkalis (alkaline substances)	+	Cresylic acid	-
Hydrocarbons, aliphatic (petroleum derivatives)	+	Magnesium hydroxide	+
Formic acid >10 % (methanoic acid)	-	Maleic acid (cis-ethylenedicarboxylic acid)	+
Ammonia anhydrous 25%	+	Methanol (methyl alcohol ) <85 %	-
Amyl acetate	+	Mineral oil	+
Amyl alcohol	+	Naphthalene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Naphthene	-
Barium hydroxide	+	Sodium carbonate (soda)	+
Petrol (92-100 octane)	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Hydrobromic acid <10 %	+	Sodium chloride (table salt)	+
Butyl acetate	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl alcohol	+	Caustic soda	+
Calcium hydroxide (slaked lime)	+	Heating oil, diesel	+
Chloroacetic acid	-	Oxalic acid <25 % (ethanedioic acid)	+
Chloroform (trichlormethane)	o	Perchloraethylene	o
Chlorosulphuric acid (wet and dry)	-	Kerosene	+
Chlorinated water (swimming pool concentration)	+	Oils, vegetable and animal	+
Hydrochloric acid	+	Phosphoric acid <5%	+
Chromium bath	+	Phthalic acid, phthalic anhydride	+
Chromic acid	+	Crude oil	+
Diesel fuels	+	Nitric acid <5%	o
Mineral oil and mineral oil products	+	Hydrochloric acid <10 %	+
Acetic acid diluted <5%	+	Sulphur dioxide (wet and dry)	+
Ethanol <85 % (ethyl alcohol)	+	Carbon disulphide	+
Greases, oils and waxes	+	Sulphuric acid <5%	o
Hydrofluoric acid diluted	o	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Trichloroethylene	o
Impregnating oils	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Potash	+	Xylene	-

+ = resistant 0 = for a limited time - = not resistant \*The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

#### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 10 2924 871  
info@weicon.it

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr