

# Belt Repair-Kit SF



**pasty | fast-curing | highly elastic | wear-resistant | impact- and abrasion resistant | high resistance to chemicals and pressure**

WEICON Belt Repair-Kit is a 2-component polyurethane system for the fast repair and coating of rubber surfaces.

It has a very high curing speed, high elasticity and wear resistance, is impact-resistant and abrasion-resistant, and has a particularly high tear resistance. Thanks to its high mechanical strength, it is suitable especially for repairs on rubber and metal components, which are exposed to impacts, abrasion or vibrations.

The Belt Repair-Kit SF offers fast and easy processability. The system is suitable for various applications, such as the repair and coating of conveyor belts, the repair of rubber coatings, for use as flexible wear protection, and for the fast repair of worn-out rubber surfaces.

In addition to the polyurethane system, the set comprises a primer for surface pre-treatment, and a spatula to spread the compound evenly.

## Technical data Primer

Colour	black
Density of the mixture	0,9 g/cm <sup>3</sup>
Colour after curing PU	black

## Technical data Urea

Base	polyurea
Colour after curing PU	black
Minimum shelf life	at room temperature 12 mon.
Density of the mixture	1,1 g/cm <sup>3</sup>
Consumption	Layer thickness 1.0 mm 1,1 kg/m <sup>2</sup>
Mixing ratio by weight PU	10:100
Texture	pasty
Pot life PU	20°C 3 min.
Working strength/demouldable after PU	20 °C 1 h
Final strength PU	(100 % strength) 3 h
Hardness (Shore A) PU	85±3
Tensile strength PU	DIN EN ISO 527 8,4 N/mm <sup>2</sup>
Elongation at break (tensile) PU	DIN EN ISO 527-2 590
Tear resistance PU	31 kN/m
Approvals / Guidelines	
MIL-Spec	complies with MIL-A-47284A

## Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

## Surface Pre-Treatment

The successful application of the WEICON Belt Repair-Kit SF depends on the thorough pre-treatment of all surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture have a negative impact on the adhesion of polyurethane resins. Best results are achieved with application on clean, rigid and thoroughly roughened surfaces. Prior to the application of WEICON Belt Repair-Kit SF, the following points must be strictly observed:

### Cleaning

Surfaces must be clean, dry and free of grease. First remove any surface soiling, like dust, dirt, oil and grease, with WEICON Surface Cleaner.

### Roughening

Then mechanically roughen the clean surface with coarse abrasives (twist knot wire wheel, wire brush, diamond blade) thoroughly. While doing so, apply gentle pressure evenly to the surface in order to prevent the rubber from overheating. Brush off any loose dirt from the surface, then clean again with WEICON Surface Cleaner.

### Surface pre-treatment with 1K Primer G

1K Primer G is a 1-component system that must be stirred carefully before application until a homogeneous, viscous, black mass is obtained. Apply 1K Primer G to the clean, dry and roughened surface and spread it evenly with a brush. Allow the primer to flash off until the solvent has evaporated

## Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

# Belt Repair-Kit SF

## Belt Repair-Kit SF

and the layer looks dry (after approximately 5–15 minutes, depending on ambient temperature and humidity).

### Mixing

With the help of the provided static mixer, the product can be applied straight from the double cartridge. Discard the first five centimetres of the dispensed bead, then apply Urethane 85 SF evenly to the primed surface.

### Application

For a pre-coating, use the Contour Spatula Flexy to intensely work the Urethane 85 into the surface to achieve maximum adhesion. Immediately after pre-coating, fill the areas that need treatment completely with the compound and spread it evenly.

### Storage

WEICON Urethane should be stored at room temperature in a dry place. Unopened containers can be stored at temperatures of +18 °C to +25 °C and a relative humidity of < 70 %. Opened containers must be used up within 3 months.

### Accessories

10057514	Dispenser 2C 10:1 Standard, 1 PCE
10104191	1K Primer G, 50 ml, black
10057191	Mixing Nozzle MFHX, 1 PCE, orange
10022562	Processing Spatula, 1 PCE
10010887	Processing Spatula, 1 PCE
10010066	Contour Spatula Flexy, 1 PCE
10032350	Primer Applicator, 1 PCE

### Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	Nm x 0.738 = lb·ft
µm/25.4 = mil	Nm x 141.62 = oz·in
N x 0.225 = lb	mPa·s = cP
N/mm² x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

### Available sizes

10062980 Belt Repair-Kit SF, 0,59 kg

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 20 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr