

WEICON Food Grade



surface coating | food safety certification | drinking water approval according to BS 6920

WEICON Food Grade is a system for surface coating and is approved by the Ruhr District Institute of Hygiene for contact with aqueous and fatty foods up to 70 °C. It is used both for coating surfaces and as an adhesive. The flowable 2-component epoxy resin system has a high proportion of fine mineral fillers. The coating is easy to apply and adheres to a wide variety of surfaces, even under mechanical stress. Food Grade has very good chemical resistance and is suitable for coating a wide variety of parts such as pumps, conveyor systems, lifting screws, hoppers, tanks and pipes.

Because of its food approval, the coating is suitable for applications in the drinking water sector, in the beverage industry, in the pharmaceutical industry, in the chemical industry, in commercial kitchens, bakeries or in food production.

WEICON Food Grade is suitable on its own or in combination with one of the other WEICON Plastic Metal types for a system build-up.

Characteristics

Base	epoxy
Filler	mineral
Texture	flowable
Colour	white
Minimum shelf life	at room temperature
	24 mon.

Processing

Processing temperature	+15 °C to +40 °C
Component temperature	>3 °C above dew point
Relative air humidity	< 85 %
Mixing ratio by weight	100:18
Mixing ratio by volume	100:34
Viscosity of the mixture	at +25 °C
Density of the mixture	35.000-40.000 mPa·s
Consumption	1.7 g/cm³
Max. layer thickness	Layer thickness 1.0 mm
	1.7 kg/m²
	10 mm

Curing

Pot life	at 20 °C, 500 g batch	30 min.
Additional layer after	(35 % strength)	5 h
Working strength after	(80 % strength)	8 h
Final strength	(100 % strength)	24 h
Shrinkage		0,28 %

Mechanical properties after curing

- Measured after curing at	24 h RT + 24 h 60 °C	
Tensile strength	DIN EN ISO 527-2	46 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	0,9 %
E-modulus (tensile)	DIN EN ISO 527-2	5300-5700 MPa
Compressive strength	DIN EN ISO 604	95 MPa
Bending strength	DIN EN ISO 178	71 MPa
Hardness (Shore D)	DIN ISO 7619	86±3
Adhesive strength	DIN EN ISO 4624	19,4 MPa
Taber Test	DIN ISO 9352 (H18, 1 kg, 1000 rotations)	1,3 g / 0,8 cm³
Lap shear strength material thickn. 1,5mm DIN EN 1465		
Steel 1.0338 sandblasted		19 MPa
Stainless steel V2A sandblasted		23 MPa
Aluminium sandblasted		9 MPa
Galvanized steel		7 MPa

Thermal parameters

Temperature resistance	-35 °C to +120 °C
Tg after curing at room temperature	(DSC) 52 °C
Tg after tempering (at 120°C)	(DSC) 69 °C
Heat deflection resistance	DIN EN ISO 75-2 65 °C
Thermal conductivity	DIN EN ISO 22007-4 0,632 W/m·K
Heat capacity	DIN EN ISO 22007-4 1,185 J/(g·K)

Electrical parameters

Resistance	DIN EN 62631-3-1	2,94 · 10^14 Ω·m
Magnetic		no

Approvals / Guidelines

MIL-Spec	complies with	MIL-A-47284A
Food safety certification		BS 6920

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface Pre-Treatment

The successful application of WEICON Food Grade depends on the thorough pre-treatment of the surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Food Grade

on the adhesion. Therefore, before processing WEICON Food Grade, the following points must be observed: The areas to be bonded or repaired must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S.

Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 1/2 - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON Food Grade, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6). The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m². Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture. After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied. Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500. After the surface pre-treatment, WEICON Food Grade should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

Mixing

First, stir the resin. Then mix the resin and hardener together thoroughly and bubble-free for at least four minutes at 20 °C (68 °F). The included processing spatula or a mechanical mixer, such as a mortar stirrer, can be used for this purpose. With mechanical mixers, a low speed of max. 500 rpm should be used. The components should be stirred until a homogeneous mixture is achieved. The mixing ratio of the two components must be strictly observed, as otherwise, strongly deviating physical values will result (max. deviation +/- 2%). Only prepare a batch as large as can be processed within the pot life of 30 minutes. The specified pot life refers to a material batch of 500 g and 20 °C (68 °F) material temperature. Mixing larger quantities or higher processing temperatures will result in faster curing due to the typical reaction heat of epoxy resins.


Application

For processing, we recommend an ambient temperature of 20 °C (68 °F) at less than 85% relative humidity. For a thin

pre-coat, work WEICON Food Grade intensively into the surface in crosswise layers using the Contour Spatula Flexy to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, further applications can be carried out straight away, until the desired layer thickness is reached. Make sure that the epoxy resin is applied evenly and without air bubbles. To fill large gaps or holes, fibreglass, expanded metal or other mechanical fixing materials should be used. Finally, the surface can be smoothed easily with the help of a PE film and a rubber roller.

Curing

Final hardness is reached after 48 hours at 20 °C (68 °F) at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40 °C (104 °F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time. The following rule of thumb applies: Each increase by +10 °C (50 °F) above room temperature (20 °C/68 °F) will decrease the curing time by half. Temperatures below 16 °C (61 °F) increase the curing time, until at approx. 5 °C (41 °F) and below, almost no reaction will take place at all.



Storage

WEICON Epoxy Resin Systems should be stored in a dry place at room temperature. Unopened containers can be stored at temperatures from +18 °C to +28 °C. Opened containers must be used up within 6 months.

Scope of delivery

Processing Spatula | Instructions for use | Gloves | Resin & Hardener

Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Food Grade

Accessories

10000147	Cleaner Spray S, 500 ml, transparent
10000347	Cleaner S, 5 L, colourless, transparent
10024313	Surface Cleaner, 400 ml, transparent
10025288	Surface Cleaner, 5 L, transparent
10026647	Mould Release Agent Liquid F 1000, 250 ml, white, milky
10026712	Mould Release Agent Wax P 500, 150 g
10053995	Repair Stick Multi-Purpose, 115 g, vintage white
10000913	Glass Fibre Cloth Tape, 1 PCE, white
10010887	Processing Spatula, 1 PCE
10022562	Processing Spatula, 1 PCE
10059417	Brush 35 short, flat, Plastic Metal, 1 PCE
10001978	Stirrer Stainless Steel, 1 PCE
10016002	Pump Dispenser WPS 1500, 1 PCE
10000441	Cartridge Gun, 1 PCE
10002034	Empty cartridge, 1 PCE
10039667	Cable Scissors No. 35, 1 PCE
10045523	Processing Kit, 1 PCE

Recommended equipment

Angle grinder	Fabric tape
Blast machine	Brush
Heat pocket	Foam roller
Hot or fan heater	Rubber roller
Smoothing trowel, spatula	Lint-free cloth
PE film 0.2 mm	

Conversion table

(°C x 1.8) + 32 = °F	Nm x 8.851 = lb·in
mm/25.4 = inch	Nm x 0.738 = lb·ft
µm/25.4 = mil	Nm x 141.62 = oz·in
N x 0.225 = lb	mPa·s = cP
N/mm² x 145 = psi	N/cm x 0.571 = lb/in
MPa x 145 = psi	kV/mm x 25.4 = V/mil

Available sizes

10062864	WEICON Food Grade, 200 g, white
10062869	WEICON Food Grade, 500 g, white
10062875	WEICON Food Grade, 2 kg, white

	WEICON A	WEICON B	WEICON BR	WEICON C	WEICON F	WEICON F2	WEICON HB 300	WEICON HT 111	WEICON SF	WEICON ST	WEICON TI	WEICON UW	WEICON WR2	WEICON HP	WEICON Fire Safe	WEICON Anti-Static	WEICON Food Grade	WEICON Anti-Stick	WEICON Ceramic BL	WEICON GL	WEICON Ceramic HC 220	WEICON GL-S	WEICON Ceramic W	WEICON WP	WEICON WR	WEICON GBC
Repair and moulding	x	x	x	x	x	x	x	x	x	x	x	x	x													
Adhesive				x	x		x	x		x				x	x											
Wear, erosion and corrosion protection – abrasion-resistant coating																x	x	x	x	x	x	x	x	x		
Casting, relining and gap compensation – casting and injecting potting compound	x					x							x											x	x	

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Food Grade

Chemical resistance after curing* (Excerpt)

Exhaust fumes	+	Potassium carbonate	+
Acetone	o	Potassium hydroxide 0-20 % (caustic potash)	+
Ethyl ether	+	Milk of lime	+
Ethyl alcohol	o	Carbolic acid	-
Ethylbenzene	-	Creosote oil	-
Alkalies (alkaline substances)	+	Cresylic acid	-
Hydrocarbons, aliphatic (petroleum derivatives)	+	Magnesium hydroxide	+
Formic acid >10 % (methanoic acid)	-	Maleic acid (cis-ethylenedicarboxylic acid)	+
Ammonia anhydrous 25%	+	Methanol (methyl alcohol) <85 %	-
Amyl acetate	+	Mineral oil	+
Amyl alcohol	+	Naphthalene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Naphthene	-
Barium hydroxide	+	Sodium carbonate (soda)	+
Petrol (92-100 octane)	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Hydrobromic acid <10 %	+	Sodium chloride (table salt)	+
Butyl acetate	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl alcohol	+	Caustic soda	+
Calcium hydroxide (slaked lime)	+	Heating oil, diesel	+
Chloroacetic acid	-	Oxalic acid <25 % (ethanedioic acid)	+
Chloroform (trichlormethane)	o	Perchloroethylene	o
Chlorosulphuric acid (wet and dry)	-	Kerosene	+
Chlorinated water (swimming pool concentration)	+	Oils, vegetable and animal	+
Hydrochloric acid	+	Phosphoric acid <5%	+
Chromium bath	+	Phthalic acid, phthalic anhydride	+
Chromic acid	+	Crude oil	+
Diesel fuels	+	Nitric acid <5%	o
Mineral oil and mineral oil products	+	Hydrochloric acid <10 %	+
Acetic acid diluted <5%	+	Sulphur dioxide (wet and dry)	+
Ethanol <85 % (ethyl alcohol)	+	Carbon disulphide	+
Greases, oils and waxes	+	Sulphuric acid <5%	o
Hydrofluoric acid diluted	o	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Trichloroethylene	o
Impregnating oils	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Potash	+	Xylene	-

+ = resistant 0 = for a limited time - = not resistant *The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.