

Glass Fibre Cloth Tape



Improves adhesion and pressure resistance

Improves adhesion and compressive strength of WEICON Epoxy Resins in many repair and maintenance works. Dimensions: 1000 x 50 mm

Characteristics

Base	Glass fibre
Colour	white
Minimum shelf life	at room temperature ∞ mon.
Width	50 mm
Length	1.000 mm

Mechanical properties after curing

Gross weight	DIN EN 12127	220 g/m ²
Warp thread count	EN 1049-2	12,0 Fd./cm
Warp yarn fineness	DIN 53830-3	EC9-68 Tex
Warp tensile strength	EN ISO 13934-1	420 N/cm
Weft thread count	EN 1049-2	9,5 Fd./cm
Weft yarn fineness	DIN 53830-3	EC11-136 Tex
Weft tensile strength	EN ISO 13934-1	640 N/cm

Thermal parameters

Temperature resistance	+ 500 °C
------------------------	----------

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Scope of delivery

Glass Fibre Cloth Tape

Available sizes

10000913 Glass Fibre Cloth Tape, 1 PCE, white

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr