

# Glass Fibre Cloth Tape



## Improves adhesion and pressure resistance

Improves adhesion and compressive strength of WEICON Epoxy Resins in many repair and maintenance works.  
Dimensions: 1000 x 50 mm

### Characteristics

Base	Glass fibre	
Colour	white	
Minimum shelf life	at room temperature	∞ mon.
Width	50 mm	
Length	1.000 mm	

### Mechanical properties after curing

Gross weight	DIN EN 12127	220 g/m <sup>2</sup>
Warp thread count	EN 1049-2	12,0 Fd./cm
Warp yarn fineness	DIN 53830-3	EC9-68 Tex
Warp tensile strength	EN ISO 13934-1	420 N/cm
Weft thread count	EN 1049-2	9,5 Fd./cm
Weft yarn fineness	DIN 53830-3	EC11-136 Tex
Weft tensile strength	EN ISO 13934-1	640 N/cm

### Thermal parameters

Temperature resistance	+ 500 °C
------------------------	----------

### Approvals / Guidelines

MIL-Spec	complies with	MIL-T-83523
----------	---------------	-------------

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr