

WEICONLOCK® AN 301-72 Pipe and Flange Sealing



Certified to
NSF/ANSI 61



Pipe and flange sealing with PTFE | classified as non-hazardous | high-temperature-resistant | drinking water and DVGW approval

- higher viscosity
- medium strength
- disassembly with normal tools

Technical Data

| | |
|--|--------------------------|
| Colour | white |
| Fluorescent | yes |
| For thread connections up to | M 80 R 3" |
| Viscosity | 15.000 - 60.000 ht mPa·s |
| Gap bridging up to max. | 0,3 mm |
| Breakaway torque | 5 - 10 Nm |
| Prevail torque | 4 - 6 Nm |
| Shear strength Nmm ² (DIN 54452) | 5 - 7 N/mm ² |
| Handling strength | 15 - 30 min. |
| Final strength (100 % strength) | 6-12 h |
| Temperature resistance | -60 °C to +200 °C |
| Compressive strength (free cutting steel / grub screw = 8.8) | |
| M_3x6 max. | 1500 bar |
| M_4x6 max. | 1500 bar |
| M_5x8 max. | 1250 bar |
| M_6x10 max. | 1250 bar |
| M_8x12 max. | 700 bar |
| M_10x16 max. | 500 bar |

Anaerobic Adhesives and Sealants

Surface pre-treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. Apply WEICONLOCK to the thread in circles. Screw the pipe thread together and tighten it to the desired alignment. When used as flange sealing, apply a continuous bead to one flange side, then assemble parts quickly and screw tight. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

WEICONLOCK has a shelf life of at least 24 months, when stored at room temperature in closed original container. Protect from heat sources and direct sunlight. The air contained in the Pen keeps WEICONLOCK liquid.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

- 10021433 Activator F, 200 ml, green
- 10001256 Dosing Tip, 1 PCE

Available sizes

- 10026836 WEICONLOCK® AN 301-72 Pipe and Flange Sealing, 50 ml, white
- 10026840 WEICONLOCK® AN 301-72 Pipe and Flange Sealing, 200 ml, white

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.