Flex 310 M[®] Classic MS-Polymer

Suitable for universal use | ISEGA-certified

WEICON Flex 310 M Classic is strong, paintable (wet-onwet), sandable, has an outstanding resistance to ageing and good resistance to UV rays. It is resistant to fresh and salt water and is free of silicone, isocyanate, halogens and solvents. The product as an ISEGA certificate and can be used as an adhesive in the food technology. Flex 310 M Classic is an elastic adhesive based on MS polymer and is suitable for the bonding of metals, many plastics, ceramics, wood, glass and stone. This adhesive and sealant can be used in metal construction, tank and apparatus engineering, carriage, vehicle and container construction, ventilation and air conditioning systems, in the electrical industry, yacht and boat construction, and in all applications where silicones or products containing silicones are not suitable. Elastic adhesives and sealants

MS-Polymers

W E I C O N

Technical Data

| Base | | 1 C. polyoxypropylene |
|---|----------------------------|---|
| Texture | | pasty |
| Can be painted | | only "wet into the wet" within 3 h at the latest |
| Cure type | | moisture-curing |
| Stability/run-off | ASTM D 2202 | 1.0 mm |
| Density | | 1,44 g/cm ³ |
| Curing condition | | from +5°C to +40°C and 30% to 95% rel. air air humidity |
| Processing temperature | | +5°C to +40°C |
| Curing speed | in the first 24 h | 2 - 3 mm |
| Skin-over time | | 25 min. |
| Gap bridging up to max. | | 5 mm |
| Max. sealing joint width | | 25 mm |
| Tensile strength | ISO 37 / S3A | 3,3 N/mm² |
| Tensile strength of the pure adhesive and sealant | ISO 37 | 3,3 N/mm² |
| Elongation at break (tensile) | DIN 53504/ASTM D412 | 650 % |
| Medium lap shear strength (DIN EN 1465/ASTM D 1002) | | 2,1 N/mm ² |
| Tear resistance | DIN 53515 / ASTM D 1002 | 20 kN/m |
| Volume change | DIN 52451 | -1 % |
| Hardness (Shore A) | DIN ISO 7619 | 42±5 |
| Temperature resistance | | -40 °C to +90 °C, briefly up to +130 °C |
| Tg after curing at room temperature | | ~ -55 °C |
| Resistance | 2.3 mm layer thickness | 1,0 x 10¹ ⁰ Ω·m |
| Specific resistance | | > 10 ¹⁰ Ω·cm |
| Dielectric strength | DIN EN 60243-1 (20°C) | 13,07 kV/mm |
| Tracking resistance | DIN EN 60112 | CTI 800 |
| Building material class | DIN 4102 | B 2 |
| Minimum shelf life | at room temperature | 12 mon. |
| Approvals / Guidelines | | |
| ISSA Code | | 75.634.30/31/32 |
| IMPA Code | | 815271/72/73 |

Surface Pre-Treatment

Surfaces must be clean and free of grease. Many surface soilings, such as oil, grease, dust and dirt can be removed with WEICON

Surface Cleaner. For heavily soiled metal surfaces, we recommend Cleaner Spray S; for removing old colour residues or adhesive

residues, WEICON Sealant and Adhesive Remover is ideal. Most materials can be bonded to and among each other. For certain materials or special requirements, we recommend the use of a

bonding agent (primer). Mechanical surface pre-treatment e.g. by grinding or sanding can also improve the adhesion considerably.

Processing

Application methods Cartridge gun for 310 ml cartridges, compressed air gun, we recommend a version with piston rod

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

> WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it

WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Türkiye phone +90 (0) 212 465 33 65 info@weicon.com.tr

Flex 310 M[®] Classic MS-Polymer

(WEICON Compressed Air Cartridge Gun), automatic dosing systems. Joining the components In order to guarantee and ideal wetting, the bonding parts need to be joined, before the adhesive skins over (skin-over time).

Ageing

The test specimens were artificially aged according to DIN ISO 21194, Annex A, to assess their long-term durability.

After artificial ageing, Flex 310 M Classic with Primer K 200 or Activating Cleaner achieved grade 1 in the bead peel test on aluminium.

Grade 1 means: more than 95% cohesive failure and less than 5% adhesive failure in the form of the adhesive peeling off the contact surface.

After artificial ageing, Flex 310 M Classic with Primer K 200 or Activating Cleaner achieved grade 2 in the bead peel test on stainless steel (V2A).

Grade 2 means: 75 % to 95 % cohesive failure.

Storage

Store in the unopened original container at room temperature. Avoid sources of heat and direct sunlight.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

- 10033114 Compressed Air Cartridge Gun, 1 PCE
- 10020751 Cartridge Gun Special, 1 PCE
- 10000441 Cartridge Gun, 1 PCE

Elastic adhesives and sealants

Available sizes

| 10002576 10010024 10010026 10057238 10057240 10057245 | Flex 310 M [®] Classic MS-Polymer, 310 ml, white Flex 310 M [®] Classic MS-Polymer, 310 ml, black Flex 310 M [®] Classic MS-Polymer, 310 ml, grey Flex 310 M [®] Classic MS-Polymer, 200 ml, white Flex 310 M [®] Classic MS-Polymer, 200 ml, grey Flex 310 M [®] Classic MS-Polymer, 200 ml, black |
|--|--|
| 10103997 | Flex 310 M [®] Classic MS-Polymer, 280 ml, black |
| 10104007 | Flex 310 M [®] Classic MS-Polymer, 280 ml, grey |
| 10104011 | Flex 310 M [®] Classic MS-Polymer, 280 ml, white |
| 10104049 | Flex 310 M [®] Classic MS-Polymer, 1 Set, white |
| 10104051 | Flex 310 M [®] Classic MS-Polymer, 1 Set, black |
| 10104053 | Flex 310 M [®] Classic MS-Polymer, 1 Set, grey |
| 10104486 | Flex 310 M [®] Classic MS-Polymer, 1 Set (10 x |
| | 280ml), white |
| 10104490 | Flex 310 M [®] Classic MS-Polymer, 1 Set (10 x |
| | 280ml), grey |
| 10104491 | Flex 310 M [®] Classic MS-Polymer, 1 Set (10 x |

280ml), black

To the product detail



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarante the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

WEICON Ibérica S.L. Spain phone +34 (0) 914 7997 34 info@weicon.es WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL Romania phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Türkiye phone +90 (0) 212 465 33 65 info@weicon.com.tr