

CA-Activator Spray AC



Nonfood Compounds
Program Listed P1
Registration 155052

**Acetone-based curing activator for cyanoacrylate adhesives
no blooming**

The activator speeds up the curing process of WEICON Contact Cyanoacrylate Adhesives.

When applied to absorbing surfaces, e.g. wood or foam etc., and all chemically-treated surfaces, e.g. zinc galvanized metals etc., the activator's effectiveness lasts approx. one minute.

On non-absorbent surfaces, the activator's effectiveness lasts up to approx. 12 hours.

Use is recommendable with: highly viscous WEICON Contact types, large thickness of the adhesive layer, absorbing and porous surfaces, passive materials (alkaline surfaces, like for example zinc coated metal parts), disadvantageous environmental conditions (low temperatures, low air humidity < 30%).

Characteristics

Silicone-free	yes
Minimum shelf life	at room temperature 12 mon.

Processing

Processing temperature	+10°C to +30°C
------------------------	----------------

Approvals / Guidelines

MIL-Spec	complies with	MIL-T-83523
----------	---------------	-------------

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 521 9322 0
info@weicon.de

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr