

CA Primer for Polyolefines



Using the WEICON O-Ring Bonding Set, sealing rings out of all common materials can be produced in no time.

Without pre-treatment, many plastics cannot be bonded or bond only under certain conditions. When these plastics are pre-treated with WEICON Contact Primer, their surface structure changes. Thereby, the joining of materials like polyethylene (PE) and polypropylene (PP), belonging to the polyolefine group, is made possible. Even modern thermoplastic elastomers (TPE), PTFE and related plastics as well as silicones can be bonded, when pre-treated with WEICON Contact Primer.

Characteristics

Minimum shelf life	at room temperature	12 mon.
--------------------	---------------------	---------

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface Pre-Treatment

For a flawless adhesive bond, surfaces must be clean and dry (clean and degrease with WEICON Surface Cleaner). Smooth surfaces should be roughened mechanically. To improve the adhesion of plastics difficult to bond (e.g. PE, PP, POM, PTFE), thermoplastic elastomers (TPE) and silicones, WEICON CA-Primer can be applied to the bonding surface.

Application

Brush or spray a thin layer onto the bonding surfaces and allow to flash off briefly. Apply cyanoacrylate adhesives and join parts.

Scope of delivery

Primer

Available sizes

10000275 CA Primer for Polyolefines, 10 ml

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr