

# Crack Testing Agent Penetrant



## Diffusion agent for the non-destructive material testing by means of colour penetrant inspection

Red dye penetrant with excellent capillary action for non-destructive material testing - washes off with solvent. Suitable for metals, many plastics, ceramic materials, glass etc. The suitability for plastic has to be tested in advance.

### Technical data

Odour	solvent
Colour	red
Specific properties	very good capillary action
Silicone-free	yes
Processing temperature	0 °C bis +50 °C
contact time	5 min.
Minimum shelf life	at room temperature
Temperature resistance	24 mon.
0 °C to +50 °C	
<b>Approvals / Guidelines</b>	
MIL-Spec	complies with
	MIL-T-83523

### Application

1. Thoroughly remove grease, oil or other contaminants from parts with WEICON Crack Testing Agent Cleaner and dry them off. The flawed areas must be open towards the surface.
2. The processing temperature should be between 0°C to +50°C. Apply WEICON Crack Testing Agent Penetrant to the cleaned and dry surface and allow to take effect for 5 - 10 minutes.
3. Remove excess penetrant from the surface with a lint-free cloth and slightly moistened with WEICON Crack Testing Agent Cleaner.
4. Apply WEICON Crack Testing Agent Developer from a distance of approx. 20 cm. Spray on just enough developer to create a white background on the surface. Too much developer can hide fine cracks! After a short time, cracks and defects become visible as red lines and dots. After 5 - 10 minutes, make the final visual inspection.

### Storage

Container is pressurised. Protect from direct sunlight and temperatures above +50 °C.

### Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets ([www.weicon.com](http://www.weicon.com)) must be observed.

### Available sizes

10047461 Crack Testing Agent Penetrant, 500 ml, red

To the product detail page:



### Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.  
United Arab Emirates  
phone +971 4 880 25 05  
info@weicon.ae

WEICON Inc.  
Canada  
phone +1 877 620 8889  
info@weicon.ca

WEICON Czech Republic s.r.o.  
Czech Republic  
phone +42 (0) 417 533 013  
info@weicon.cz

WEICON Ibérica S.L.  
Spain  
phone +34 (0) 914 7997 34  
info@weicon.es

WEICON GmbH & Co. KG  
(Headquarters) Germany  
phone +49 (0) 251 9322 0  
info@weicon.de

WEICON Italia S.r.l.  
Italy  
phone +39 (0) 010 2924 871  
info@weicon.it

WEICON Romania SRL  
Romania  
phone +40 (0) 3 65 730 763  
office@weicon.com

WEICON SA (Pty) Ltd  
South Africa  
phone +27 (0) 21 709 0088  
info@weicon.co.za

WEICON South East Asia Pte Ltd  
Singapore  
Phone (+65) 6710 7671  
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.  
Türkiye  
phone +90 (0) 212 465 33 65  
info@weicon.com.tr