

Mould Release Agent Liquid F 1000



for release processes from smooth and non-absorbent surfaces

F 1000 is a release agent based on wax for epoxy resins and polyurethanes. It is particularly suitable for release processes from smooth and non-absorbing surfaces.

Characteristics

Base	Wax, containing solvent
Colour	white, milky
Minimum shelf life	at room temperature 24 mon.

Processing

Processing temperature	+15 to +25
Consumption	50 - 100 ml/m ²

Thermal parameters

Temperature resistance	to +70
------------------------	--------

Approvals / Guidelines

ISSA Code	75.509.36
IMPA Code	812959/60

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface Pre-Treatment

The surface to be treated must be clean, dry and free of grease (e.g. clean and degrease with WEICON Surface Cleaner).

Application

Apply Mould Release Agent Liquid F 1000 with a fibre-free cellulose cloth, lint-free paper towel, brush or WEICON Primer Applicator and allow to dry. For new components, the application should be repeated two to three times. After application, allow to dry for approx. 10 minutes until the surface is matt, dry and does not stick. Do not treat absorbent or porous surfaces with mould release agent (use Mould Release Agent Wax P 500, if required).

Storage

Store at room temperature in a dry place. Unopened containers can be stored at temperatures from +18 °C to +25 °C. Protect from direct sunlight.

Scope of delivery

Substance

Available sizes

10026167	Mould Release Agent Liquid F 1000, 1 L, white, milky
10026647	Mould Release Agent Liquid F 1000, 250 ml, white, milky

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr