

WEICON WL



surface coating / excellent base coat for stainless steel surfaces / with residual elasticity

The WEICON WL epoxy resin system is used to coat surfaces that are subject to stresses. It has a high adhesive strength, especially on stainless steel. It is liquid, sprayable, spreadable (can be applied with a brush), self-levelling, retains residual elasticity, is ceramic-filled and chemical-resistant.

Owing to its long pot life, WEICON WL can be used for applications with higher ambient temperatures or for larger surfaces. Due to the high flowability of WEICON WL, it is important to ensure a low layer thickness and to observe the layer sequence time.

WEICON WL is well suited for a system build-up in combination with other Plastic Metal types.

For example, the 2-component epoxy resin can be used as a primer when lining pump casings made of stainless steel that are subject to heavy stress. The surface coating can be used in the field of wastewater technology, on pumps, in water pumping, in mechanical and plant engineering, in apparatus engineering and in many other areas of industry.

Characteristics

Base	Epoxy
Filler	ceramic
Texture	liquid
Colour after curing	white
Minimum shelf life	at room temperature 24 mon.

Processing

Processing temperature	+15 °C to +40 °C	
Component temperature	>3 °C above dew point	
Relative air humidity	< 85 %	
Mixing ratio by weight	100:22	
Mixing ratio by volume	100:46	
Viscosity of the mixture	at +25 °C	~ 7.000 mPa·s
Density of the mixture	1,7 g/cm ³	
Consumption	Layer thickness 1.0 mm	1,7 kg/m ²
Max. layer thickness	per step	20 mm

Curing

Pot life	at 20 °C, 500 g batch	~ 70 min.
Additional layer after	(35 % strength)	8 h
Working strength after	(80 % strength)	18 h
Final strength	(100 % strength)	36 h
Shrinkage	0,04 %	

Mechanical properties after curing

- Measured after curing at		24 h RT + 24 h 60 °C
Tensile strength	DIN EN ISO 527-2	35 MPa
Elongation at break (tensile)	DIN EN ISO 527-2	2,2 %
E-modulus (tensile)	DIN EN ISO 527-2	2400-2700 MPa
Compressive strength	DIN EN ISO 604	67 MPa
Bending strength	DIN EN ISO 178	39 MPa
Hardness (Shore D)	DIN ISO 7619	80±3
Adhesive strength	DIN EN ISO 4624	15 MPa
Taber Test	DIN ISO 9352 (H18, 2 x 1 kg, 1000 rotations)	0,9 g / 0,55 cm ³

Lap shear strength material thicken. 1,5mm DIN EN 1465		
Steel 1.0338 sandblasted	14 MPa	
Stainless steel V2A sandblasted	20 MPa	
Aluminium sandblasted	9 MPa	
Galvanized steel	4 MPa	

Thermal parameters

Temperature resistance	-35 °C to +120 °C	
Tg after curing at room temperature	(DSC)	~ 45 °C
Tg after tempering (at 120°C)	(DSC)	~ 45 °C
Heat deflection resistance	DIN EN ISO 75-2	44 °C
Thermal conductivity	DIN EN ISO 22007-4	0,87 W/m·K
Heat capacity	DIN EN ISO 22007-4	1,4 kJ/KG·K

Electrical parameters

Resistance	DIN EN 62631-3-1	7,84 · 10 ¹⁶ Ω·m
Magnetic	no	

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Surface Pre-Treatment

The successful application of WEICON WL depends on the thorough preparation of the surfaces. This is the most important factor for overall success. Dust, dirt, oil, grease, rust and moisture or wetness have a negative impact on the adhesion. Therefore, before processing WEICON WL, the

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICON WL

following points must be observed: The surfaces must be free of any oil, grease, dirt, rust, oxides, paint and other impurities or residues. For cleaning and degreasing, we recommend WEICON Cleaner Spray S.

Smooth and particularly heavily soiled surfaces should additionally be treated by mechanical surface pre-treatment, e.g. by grinding or preferably by blasting. In case of blasting, the surface should be brought to a degree of purity of SA 2 ½ - "Near White Blast Cleaning" (according to ISO 8501/1-2, NACE, SSPC, SIS). In order to achieve an optimum surface roughness of 75 - 100 µm, angular, disposable blasting media (aluminum oxide, corundum) should be used. The surface quality is negatively influenced by the use of reusable blasting media (slag, glass, quartz), but also by ice blasting. The air for blasting must be dry and oil-free. Metal parts that have come into contact with sea water or other salt solutions should first be rinsed thoroughly with demineralised water and, if possible, left to rest overnight so that all salts can be dissolved from the metal. Before each application of WEICON WL, a test for soluble salts should be carried out according to the Bresle method (DIN EN ISO 8502-6).

The maximum amount of soluble salts remaining on the substrate should not exceed 40 mg/m². Heating and repeated blasting of the surface may be necessary to remove all soluble salts and moisture.

After each mechanical pre-treatment, the surface should be cleaned again with WEICON Cleaner Spray S and protected from further contamination until the coating is applied.

Areas where no adhesion to the substrate is desired must be treated with silicone-free mould release agents. For smooth surfaces, we recommend WEICON Mould Release Agent Liquid F 1000 or, for porous surfaces, WEICON Mould Release Agent Wax P 500.

After the surface pre-treatment, WEICON WL should be applied as soon as possible (within one hour) to avoid oxidation, flash rust or new contamination.

Mixing

First, stir the resin. Then mix the resin and hardener together thoroughly and bubble-free for at least four minutes at 20°C (68°F). The included processing spatula or a mechanical mixer, such as the Stirrer Stainless Steel, can be used for this purpose. With mechanical mixers, a low speed of max. 500 rpm should be used. The components should be stirred until a homogeneous mixture is achieved. The mixing ratio of the two components must be strictly observed, as otherwise, strongly deviating physical values will result (max. deviation +/- 2 %). Only prepare a batch as large as can be processed within the pot life of 70 minutes. The indicated pot life time refers to a material batch of 500g and 20 °C (68° F) material temperature. Mixing larger quantities or higher processing

temperatures will result in faster curing due to the typical reaction heat of epoxy resins.



Application

For processing, we recommend an ambient temperature of 20 °C (68 °F) at less than 85% relative humidity. The highest adhesive strength is achieved when the parts to be processed are heated to >35 °C (>95°F) before application. For a thin pre-coat, work WEICON WL intensively into the surface in crosswise layers using a paint brush to achieve maximum adhesion. By means of this technique, the epoxy resin penetrates well into all cracks and roughness depths. Afterwards, a second application with a paint brush or foam roller can be carried out straight away, until the desired layer thickness is reached.

A layer of approx. 0,25 to 0,50 mm can be achieved per work step. Make sure that the epoxy resin is applied evenly and without air bubbles. Further coats can be applied in each case after approx. 8 hours (layer sequence time).

Curing

Final hardness is reached after 36 hours at 20 °C (68°F) at the latest. At lower temperatures, the curing can be accelerated by evenly applying heat up to max. 40 °C (104°F), e.g. with a heating pack, hot air blower or fan heater. Higher temperatures shorten the curing time.

The following rule of thumb applies: Each increase by +10 °C (50°F) above room temperature (20°C/68°F) will decrease the curing time by half. Temperatures below 16 °C (61°F) increase the curing time, until at approx. 5 °C (41°F) and below, almost no reaction will take place at all.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es


WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICON WL

Increase in strength



Storage

WEICON Epoxy Resin Systems should be stored in a dry place at room temperature. Unopened containers can be stored at temperatures from +18 °C to +28 °C. Opened containers must be used up within 6 months.

Scope of delivery

Processing Spatula | Instructions for use | Gloves | Resin & Hardener

Accessories

- 10026171 Mould Release Agent Wax P 500, 0,5 kg
- 10000147 Cleaner Spray S, 500 ml, transparent
- 10000347 Cleaner S, 5 L, colourless, transparent
- 10024313 Surface Cleaner, 400 ml, transparent
- 10025288 Surface Cleaner, 5 L, transparent
- 10026647 Mould Release Agent Liquid F 1000, 250 ml, white, milky
- 10053995 Repair Stick Multi-Purpose, 115 g, vintage white
- 10000913 Glass Fibre Cloth Tape, 1 PCE, white
- 10010887 Processing Spatula short, 1 PCE
- 10022562 Processing Spatula long, 1 PCE
- 10059417 Brush 35 short, flat, Plastic Metal, 1 PCE
- 10001978 Stirrer Stainless Steel, 1 PCE
- 10016002 Pump Dispenser WPS 1500, 1 PCE
- 10000441 Cartridge Gun, 1 PCE
- 10039667 Cable Scissors No. 35, 1 PCE
- 10045523 Processing Kit, 1 PCE

Recommended equipment

- Angle grinder
- PE film 0.2 mm
- Blast machine
- Fabric tape
- Heat pocket
- Brush
- Hot or fan heater
- Lint-free cloth
- Smoothing trowel, spatula

Conversion table

- (°C x 1.8) + 32 = °F
- Nm x 8.851 = lb·in
- mm/25.4 = inch
- Nm x 0.738 = lb·ft
- µm/25.4 = mil
- Nm x 141.62 = oz·in
- N x 0.225 = lb
- mPa·s = cP
- N/mm² x 145 = psi
- N/cm x 0.571 = lb/in
- MPa x 145 = psi
- kV/mm x 25.4 = V/mil

Available sizes

- 10067876 WEICON WL, 0,2 kg
- 10067882 WEICON WL, 0,5 kg
- 10067887 WEICON WL, 2 kg

	WEICON A	WEICON B	WEICON BR	WEICON C	WEICON F	WEICON F2	WEICON HB 300	WEICON HT 111	WEICON SF	WEICON ST	WEICON TT	WEICON UW	WEICON WR2	WEICON HP	WEICON Fire Safe	WEICON Anti-Static	WEICON Food Grade	WEICON Anti-Stick	WEICON Ceramic BL	WEICON GL	WEICON GL-S	WEICON Ceramic W	WEICON Ceramic HC 220	WEICON WP	WEICON WR	WEICON CBC
Repair and moulding	x	x	x	x	x	x	x	x	x	x	x	x	x	x												
Adhesive				x	x		x	x		x				x	x											
Wear, erosion and corrosion protection – abrasion-resistant coating																x	x	x	x	x	x	x	x	x		
Casting, relining and gap compensation – casting and injecting potting compound	x						x						x												x	x

To the product detail page:



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON WL

Chemical resistance after curing* (Excerpt)

Exhaust fumes	+	Potassium hydroxide 0-20 % (caustic potash)	+
Acetone	o	Milk of lime	+
Ethyl ether	+	Carbolic acid	-
Ethyl alcohol	o	Creosote oil	-
Ethylbenzene	-	Cresylic acid	-
Alkalis (alkaline substances)	+	Magnesium hydroxide	+
Hydrocarbons, aliphatic (petroleum derivatives)	+	Maleic acid (cis-ethylenedicarboxylic acid)	+
Formic acid >10 % (methanoic acid)	-	Methanol (methyl alcohol) <85 %	-
Ammonia anhydrous 25%	+	Mineral oil	+
Amyl acetate	+	Naphthalene	-
Amyl alcohol	+	Naphthene	-
Hydrocarbons, aromatic (benzene, toluene, xylene)	+	Sodium carbonate (soda)	+
Barium hydroxide	+	Sodium bicarbonate (sodium hydrogen carbonate)	+
Petrol (92-100 octane)	+	Sodium chloride (table salt)	+
Hydrobromic acid <10 %	+	Sodium hydroxide >20 % (caustic soda)	o
Butyl acetate	+	Caustic soda	+
Butyl alcohol	+	Heating oil, diesel	+
Calcium hydroxide (slaked lime)	+	Oxalic acid <25 % (ethanedioic acid)	+
Chloroacetic acid	-	Perchloraethylene	o
Chloroform (trichlormethane)	o	Kerosene	+
Chlorosulphuric acid (wet and dry)	-	Oils, vegetable and animal	+
Chlorinated water (swimming pool concentration)	+	Phosphoric acid <5%	+
Hydrochloric acid	+	Phthalic acid, phthalic anhydride	+
Chromium bath	+	Crude oil	+
Chromic acid	+	Nitric acid <5%	o
Diesel fuels	+	Hydrochloric acid <10 %	+
Mineral oil and mineral oil products	+	Sulphur dioxide (wet and dry)	+
Acetic acid diluted <5%	+	Carbon disulphide	+
Ethanol <85 % (ethyl alcohol)	+	Sulphuric acid <5%	o
Greases, oils and waxes	+	White spirit	+
Tannic acid diluted <7%	+	Carbon tetrachloride (tetrachloromethane)	+
Glycerin (trihydroxipropane)	+	Tetralin (tetrahydronaphthalene)	o
Glycol	o	Toluene	-
Humic acid	+	Trichloraethylene	o
Impregnating oils	+	Hydrogen peroxide <30 % (hydrogen superoxide)	+
Potash	+	Xylene	-
Potassium carbonate	+		

+ = resistant 0 = for a limited time - = not resistant *The storage of all WEICON Plastic Metal types was carried out at +20°C chemical temperature.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr