WEICON

WEICONLOCK®

WEICONLOCK® AN 301-48 Retaining Cylindrical **Assemblies**









Retaining cylindrical assemblies for bearings, shafts and bushings | high-temperature-resistant | drinking water and **DVGW** approval

- · medium viscosity
- · high strength
- · hard to disassemble

Technical Data

Colour		green		
Fluorescent		yes		
For thread connections up to		M 20 R ¾"		
Viscosity		450 - 650 nt mPa⋅s		
Gap bridging up to max.		0,15 mm		
Breakaway torque		25 - 30 Nm		
Prevail torque		40 - 55 Nm		
Shear strength Nmm ² (DIN 54452)		25 - 30 N/mm ²		
Handling strength	(35 % strength)	2 - 6 min.		
Final strength	(100 % strength)	2-4 h		
Temperature resistance		-60°C to +175°C		
Compressive strength (free cutting steel / grub screw = 8.8)				
M 3x6	max.	1500 bar		
M 4x6	max.	1500 bar		
M 5x8	max.	1500 bar		
M 6x10	max.	700 bar		
M 8x12	max.	500 bar		
M 10x16	max.	500 bar		

Anaerobic Adhesives and Sealants

Surface Pre-Treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleaned surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Processing

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. In the case of pressed joints and larger parts to be joined, both surfaces should always be wetted thinly and evenly. Join parts swiftly. For sliding seats, twist parts against each other when joining for optimum spreading of the adhesive. Bonded parts should not be moved until handling strength is reached. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Storage

WEICONLOCK has a shelf life of at least 24 months, when stored at room temperature in closed original container. Protect from heat sources and direct sunlight. The air contained in the Pen keeps WEICONLOCK liquid.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Accessories

10021433 Activator F, 200 ml, green 10001256 Dosing Tip, 1 PCE

Available sizes

10026856	WEICONLOCK [®] Cylindrical	AN	301-48	Retaining
10026857	Assemblies, 50 ml WEICONLOCK [®] Cylindrical		301-48	Retaining
10026859	Assemblies, 200 m WEICONLOCK®	nl, gree AN	en 301-48	Retaining

AN Retaining Cylindrical

Assemblies, 20 ml, green

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the requested properties are recommended. A claim cannot be derived from them.

Date of issue:28.10.2024

WEICONLOCK® AN 301-48 Retaining Cylindrical **Assemblies**



WEICONLOCK®

Anaerobic Adhesives and Sealants



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C. United Arab Emirates phone +971 4 880 25 05 info@weicon.ae

WEICON Inc. Canada phone +1 877 620 8889 info@weicon.ca WEICON Czech Republic s.r.o. Czech Republic phone +42 (0) 417 533 013 info@weicon.cz

Spain phone +34 (0) 914 7997 34 info@weicon.es

WEICON GmbH & Co. KG (Headquaters) Germany phone +49 (0) 251 9322 0 info@weicon.de

WEICON Italia S.r.L. Italy phone +39 (0) 010 2924 871 info@weicon.it WEICON Romania SRL phone +40 (0) 3 65 730 763 office@weicon.com

WEICON SA (Pty) Ltd South Africa phone +27 (0) 21 709 0088 info@weicon.co.za

WEICON South East Asia Pte Ltd Singapore Phone (+65) 6710 7671 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti. Türkiye phone +90 (0) 212 465 33 65 info@weicon.com.tr