

WEICONLOCK® AN 306-10 Retaining Cylindrical Assemblies



Retaining cylindrical assemblies for passive materials |
drinking water approval

- medium viscosity
- high strength
- hard to disassemble

Technical Data

Colour	green
Fluorescent	yes
For thread connections up to	M 20 R 3/4"
Viscosity	700 - 1.000 nt mPa·s
Processing temperature	15 - 35 °C
Gap bridging up to max.	0,15 mm
Breakaway torque	15 - 20 Nm
Prevail torque	30 - 35 Nm
Shear strength Nmm ² (DIN 54452)	25 - 35 N/mm ²
Handling strength	at room temperature
Final strength (100 % strength)	5 - 10 min.
Temperature resistance	60°C to +200°C
Minimum shelf life	at room temperature
Compressive strength (free cutting steel / grub screw = 8.8)	24 mon.
M 3x6	max.
M 4x6	max.
M 5x8	max.
M 6x10	max.
M 8x12	max.
M 10x16	max.

Approvals / Guidelines

Hygiene Institute	UBA KTW-BWGL
ISSA Code	53.402.16
IMPA Code	450836
MIL-Spec	complies with MIL-A-46106 MIL-A-46146

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 511 9322 0
info@weicon.de

WEICON Italia S.r.l.
Italy
phone +39 (0) 010 2924 871
info@weicon.it

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com


WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

WEICONLOCK® Retaining Cylindrical Assemblies

Reaction rate of various materials




Surface Pre-Treatment

To achieve optimum results, the mounting parts should be degreased and cleaned, e.g. with WEICON Surface (roughen the surfaces, if required). WEICONLOCK can also be used on uncleared surfaces, e.g. screws as delivered. However, the cleaner the surface, the better the results achieved.

Application

WEICONLOCK is applied evenly straight from the Pen with the help of the dosing tip; avoid direct contact between dosing tip/metal. In the case of pressed joints and larger parts to be joined, both surfaces should always be wetted thinly and evenly. Join parts swiftly. For sliding seats, twist parts against each other when joining for optimum spreading of the adhesive. Bonded parts should not be moved until handling strength is reached. Do not pour any WEICONLOCK back into the bottle that has already come into contact with metal. Even extremely small metal particles cause the adhesive to cure inside the bottle. Therefore, in serial production, the use of dosing devices is recommended.

Reaction speed at temp.



WEICONLOCK® AN

306-10 Retaining Cylindrical Assemblies

Retaining Cylindrical Assemblies


Storage

Store WEICONLOCK in the unopened original container at room temperature. Avoid sources of heat and direct sunlight. The air inside the packaging helps maintain storage stability.

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Strength in heat



Accessories

10021433 Activator F, 200 ml, green
 10001256 Dosing Tip, 1 PCE

Available sizes

10019911 WEICONLOCK® AN 306-10 Retaining Cylindrical Assemblies, 20 ml, green
 10014260 WEICONLOCK® AN 306-10 Retaining Cylindrical Assemblies, 50 ml, green
 10017883 WEICONLOCK® AN 306-10 Retaining Cylindrical Assemblies, 50 ml, green
 10020021 WEICONLOCK® AN 306-10 Retaining Cylindrical Assemblies, 200 ml, green

To the product detail page:



Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
 United Arab Emirates
 phone +971 4 880 25 05
 info@weicon.ae

WEICON Inc.
 Canada
 phone +1 877 620 8889
 info@weicon.ca

WEICON Czech Republic s.r.o.
 Czech Republic
 phone +42 (0) 417 533 013
 info@weicon.cz

WEICON Ibérica S.L.
 Spain
 phone +34 (0) 914 7997 34
 info@weicon.es

WEICON GmbH & Co. KG
 (Headquarters) Germany
 phone +49 (0) 251 9322 0
 info@weicon.de

WEICON Italia S.r.l.
 Italy
 phone +39 (0) 010 2924 871
 info@weicon.it

WEICON Romania SRL
 Romania
 phone +40 (0) 3 65 730 763
 office@weicon.com

WEICON SA (Pty) Ltd
 South Africa
 phone +27 (0) 21 709 0088
 info@weicon.co.za

WEICON South East Asia Pte Ltd
 Singapore
 Phone (+65) 6710 7671
 info@weicon.com.sg

WEICON Kimya Sanayi Tic. Ltd. Şti.
 Türkiye
 phone +90 (0) 212 465 33 65
 info@weicon.com.tr