

Easy-Mix S 50



resistant to high temperatures | extremely strong adhesion | very short pot life

The epoxy adhesive WEICON Easy-Mix S 50 is suitable for fast repair and maintenance work and is perfect for industrial series production with short cycle times.

The adhesive offers high temperature resistance up to +180 °C, extremely strong adhesion and high tensile strength. It is viscous, self-levelling, has a very short pot life and cures fast. After curing, the adhesive is impact- and shock-resistant. The 2-component epoxy resin system can be used on many different materials such as metal, plastic or fibre composites.

Easy-Mix S 50 can be used in a wide variety of industrial and trade applications.

The Dispenser Easy-Mix D 50 or the Manual Dispenser are required for processing Easy-Mix products in 50 ml containers.

Characteristics

Base	Epoxy
Filler	unfilled
Texture	liquid
Colour	transparent, light yellow
Minimum shelf life	at room temperature 18 mon.

Processing

Processing temperature	+15 °C to +40 °C
Component temperature	>3°C above dew point
Cure temperature	+6 °C to +40 °C
Relative air humidity	max. 85%
Mixing ratio by volume	1:1
Viscosity of the mixture	at +20 °C 4.500 mPa·s
Density of the mixture	1,2 g/cm ³
Gap bridging up to max.	2 mm

Curing

Pot life	at 20 °C, 10 g batch	4-5 min.
Handling strength	(35 % strength)	13 min.
Working strength after	(80 % strength)	20 min.
Final strength	(100 % strength)	24 h
Shrinkage		1,41 %

Mechanical properties after curing

- Measured after curing at		24 h RT + 24 h 60 °C
Tensile strength	DIN EN ISO 527-2	50 N/mm ²
Elongation at break (tensile)	DIN EN ISO 527-2	2,7 %
E-modulus (tensile)	DIN EN ISO 527-2	2.000 - 2.400 MPa
Compressive strength	DIN EN ISO 604	55 MPa
Bending strength	DIN EN ISO 178	58 MPa
Hardness (Shore D)	DIN ISO 7619	82 ± 3
Lap shear strength material thicken. 1,5mm DIN EN 1465		
	Steel 1.0338 sandblasted	22 N/mm ²
	Stainless steel V2A sandblasted	26 N/mm ²
	Aluminium sandblasted	13 N/mm ²
	Galvanized steel	16 N/mm ²
	PVC-rigid roughened	13 N/mm ²

Thermal parameters

Temperature resistance		-50 °C to +180 °C (-58 °F to +356 °F)
Tg after curing at room temperature	(DSC)	44,7 °C
Tg after tempering (at 90°C)	(DSC)	46,1 °C
Temperature conductivity		0,133 mm ² /s
Thermal conductivity	DIN EN ISO 22007-4	0,24 W/m·K
Heat capacity	DIN EN ISO 22007-4	1,482 J/(g·K)

Electrical parameters

Resistance	DIN EN 62631-3-1	1,03·10 ¹¹ Ω·m
Dielectric strength	DIN EN 60243-1 (20°C)	20 kV/mm

Approvals / Guidelines

ISSA Code	75.530.15
IMPA Code	812980

Instructions for use

When using WEICON products, the physical, safety-related, toxicological and ecological data and regulations in our EC safety data sheets (www.weicon.com) must be observed.

Note

The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.

WEICON Middle East L.L.C.
United Arab Emirates
phone +971 4 880 25 05
info@weicon.ae

WEICON Czech Republic s.r.o.
Czech Republic
phone +42 (0) 417 533 013
info@weicon.cz

WEICON GmbH & Co. KG
(Headquarters) Germany
phone +49 (0) 251 9322 0
info@weicon.de

WEICON Romania SRL
Romania
phone +40 (0) 3 65 730 763
office@weicon.com

WEICON South East Asia Pte Ltd
Singapore
Phone (+65) 6710 7671
info@weicon.com.sg

WEICON Inc.
Canada
phone +1 877 620 8889
info@weicon.ca

WEICON Ibérica S.L.
Spain
phone +34 (0) 914 7997 34
info@weicon.es


WEICON Italia S.r.l.
Italy
phone +39 (0) 10 2924 871
info@weicon.it

WEICON SA (Pty) Ltd
South Africa
phone +27 (0) 21 709 0088
info@weicon.co.za

WEICON Kimya Sanayi Tic. Ltd. Şti.
Türkiye
phone +90 (0) 212 465 33 65
info@weicon.com.tr

Easy-Mix S 50

Tensile strength after storage



Surface Pre-Treatment

Clean and dry bonding surfaces are essential for flawless adhesive bonding (e.g. cleaning and degreasing with WEICON Surface Cleaner).

Application

WEICON Easy-Mix products can be processed straight from the double cartridge by means of the included static mixer. Dismiss the first 5 cm of the adhesive bead. The adhesive is applied to just one side.

The specified pot life refers to a material batch of 10 ml at room temperature. Larger batch quantities will result in faster curing. Higher temperatures also reduce the pot life and curing time. (General rule: every increase by +10 °C above room temperature results in a decrease of the pot life and curing time by half). Temperatures below +16 °C increase the pot life and curing time significantly. From approx. +5 °C and below, no reaction takes place.

Storage

WEICON epoxy adhesives should be stored in a dry place at room temperature. Unopened containers can be stored at temperatures from +18 °C to +25 °C. Protect from direct sunlight. Failure to observe these storage instructions will reduce the shelf life to 6 months. Epoxy resins generally tend to crystallise at temperatures below +5 °C. This effect is increased by large temperature fluctuations, e.g. during transport especially in the winter months. This has a negative impact on processing, curing and technical data, can, however, be reversed by heating the product (up to max. +50 °C, no open flame). In WEICON epoxy

adhesives, crystallisation is reduced by the careful choice and combination of base resins (bisphenol A and F).

Scope of delivery

Adhesive

Accessories

- 10005237 Dispenser Easy-Mix D 50, 1 PCE
- 10005236 Quadro Mixing Nozzle A, 1 PCE, blue
- 10068261 Dosing Tip A Size 0,5 mm, 1 PCE
- 10101999 WEICON Manual Dispenser, 1 x 1:1 | 2:1

Conversion table

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{mm}/25.4 = \text{inch}$
 $\mu\text{m}/25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N}/\text{mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$

$\text{Nm} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{Nm} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{Nm} \times 141.62 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$
 $\text{N}/\text{cm} \times 0.571 = \text{lb}/\text{in}$
 $\text{kV}/\text{mm} \times 25.4 = \text{V}/\text{mil}$

Available sizes

- 10005230 Easy-Mix S 50, 50 ml, transparent, light yellow

To the product detail page:



Note
The specifications and recommendations given in this technical data sheet must not be seen as guaranteed product characteristics. They are based on our laboratory tests and on practical experience. Since individual application conditions are beyond our knowledge, control and responsibility, this information is provided without any obligation. We do guarantee the continuously high quality of our products. However, own adequate laboratory and practical tests to find out if the product in question meets the requested properties are recommended. A claim cannot be derived from them. The user bears the only responsibility for non-appropriate or other than specified applications.